



Forensic Analytical
Analytical Report

Preliminary FAX

Bulk Asbestos Analysis

(EPA Method 600/R-93-116)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B045603
Date Received: 12/05/02
Date Analyzed: 12/06/02
Date Printed: 12/06/02

Job ID / Site: Chapman Elementary School, Main Hallway

FASI Job ID: 2921-57

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
MH-1	10199615						
		Layer: Black Tar	ND				
		Layer: Black Felt	ND				
		Layer: Black Tar	ND				
		Layer: Black Felt	ND				
		Layer: Black Tar	ND				
		Layer: Black Felt	ND				
		Layer: Black Tar	ND				
		Layer: Black Felt	ND				

Total Composite Values of Fibrous Components: Asbestos:(ND)
 Cellulose (Trace%) Fibrous Glass (45%)
 Comment: Bulk complex sample.

MH-2	10199616						
		Layer: Black Tar	ND				
		Layer: Black Felt	ND				
		Layer: Black Tar	ND				
		Layer: Black Felt	ND				
		Layer: Black Tar	ND				
		Layer: Black Felt	ND				
		Layer: Black Tar	ND				
		Layer: Black Felt	ND				

Total Composite Values of Fibrous Components: Asbestos:(ND)
 Cellulose (Trace%) Fibrous Glass (45%)
 Comment: Bulk complex sample.

*C: Mary Deary
 Kip Stasell
 Bob Michael
 Rob Peters
 Sanders (3)
 Hill*

**SIX MONTH SURVEILLANCE
HOMOGENEOUS ACBM RECORDS**

Date of Inspection: 11/06/2002

District: Chico Unified School District

Inspector: Robert Peters

School: Chapman Elementary School

Building: C

Material Class	Material	Homo. Mat. #	% Asb.	F ² /L.F.	Location	Condition: Code & Comments	Friable Yes/No
M	TRANSITE PANELS		ASSUMED	UNDETERMINED	EXTERIOR	(1) (4) (12/05/01, 5/14/02 Same) <i>POOS</i>	N

School: Chapman Elementary School

Building: F

Material Class	Material	Homo. Mat. #	% Asb.	F ² /L.F.	Location	Condition: Code & Comments	Friable Yes/No
M	9" VFT		1-5%	UNDETERMINED	ROOM 3 (CLASSROOM 68)	(1) (4) (12/05/01, 5/14/02, 11/06/02 Same)	N
M	9" VFT		1-5%	UNDETERMINED	ROOM 1 (CLASSROOMS 5 & 7)	(1) (4) ↓ ↓	N
M	TRANSITE PANELS		ASSUMED	UNDETERMINED	EXTERIOR	(1) (4) ↓ ↓	N

CONDITION CODE

General Condition: (1) Good (2) Damaged (3) Significantly Damaged (25% or more)
Change in Condition: (4) No (5) Yes (if Yes, explain under comments)
Abated: (6) Repaired (7) Removed (8) Encapsulated (9) Enclosed (10) Isolated & Restricted
Miscellaneous: (11) Inaccessible, no inspection data (12) Other (Explain under comments) (13) Non-Asbestos/Not Inspected

CONSULT ORIGINAL AND SUPPLEMENTARY INSPECTION REPORTS FOR MATERIALS WITH TRACE AMOUNTS OF ASBESTOS

**SIX MONTH SURVEILLANCE
HOMOGENEOUS ACBM RECORDS**

Date of Inspection: 11/06/2002

District: Chico Unified School District

Inspector: Robert Peters

School: Chapman Elementary School

Building: G

Material Class	Material	Homo. Mat. #	% Asb.	F ² /L.F.	Location	Condition: Code & Comments	Friable Yes/No
T	MUD JOINT		1-5%	UNDETERMINED	ROOMS 1-4	(1) (4) (12/05/01, 5/14/02, 11/06/02 Same) (11) COULD NOT FIND.	N
M	TRANSITE PANELS		ASSUMED	UNDETERMINED	ROOMS 1-4		N

CONDITION CODE

General Condition: (1) Good (2) Damaged (3) Significantly Damaged (25% or more)
Change in Condition: (4) No (5) Yes (if Yes, explain under comments)
Abated: (6) Repaired (7) Removed (8) Encapsulated (9) Enclosed (10) Isolated & Restricted
Miscellaneous: (11) Inaccessible, no inspection data (12) Other (Explain under comments) (13) Non-Asbestos/Not Inspected

CONSULT ORIGINAL AND SUPPLEMENTARY INSPECTION REPORTS FOR MATERIALS WITH TRACE AMOUNTS OF ASBESTOS

**SIX MONTH SURVEILLANCE
HOMOGENEOUS ACBM RECORDS**

Date of Inspection: 05/14/2002

Inspector: Robert Peters

District: Chico Unified School District

Building: A

School: Chapman Elementary School

Material Class	Material	Homo. Mat. #	% Asb.	Ft ² /L.F.	Location	Condition: Code & Comments	Friable Yes/No
M	9" VFT		10-15%	UNDETERMINED	KITCHEN BROWN	(1) (4) PREVIOUSLY ROOM 5. (12/05/01, 5/14/02 Same)	N

School: Chapman Elementary School

Material Class	Material	Homo. Mat. #	% Asb.	Ft ² /L.F.	Location	Condition: Code & Comments	Friable Yes/No
M	TRANSITE PANELS		ASSUMED	UNDETERMINED	EXTERIOR	(1) (4) (12/05/01, 5/14/02 Same)	N

Building: B

CONDITION CODE

General Condition: (1) Good (2) Damaged (3) Significantly Damaged (25% or more)
 Change in Condition: (4) No (5) Yes (If Yes, explain under comments)
 Abated: (6) Repaired (7) Removed (8) Encapsulated (9) Enclosed (10) Isolated & Restricted
 Miscellaneous: (11) Inaccessible, no inspection data (12) Other (Explain under comments) (13) Non-Asbestos/Not Inspected

CONSULT ORIGINAL AND SUPPLEMENTARY INSPECTION REPORTS FOR MATERIALS WITH TRACE AMOUNTS OF ASBESTOS

**SIX MONTHS OF SURVEILLANCE
HOMOGENEOUS ASBESTOS RECORDS**

Date of Inspection: 05/14/2002

District: Chico Unified School District

Inspector: Robert Peters

School: Chapman Elementary School

Building: C

Material Class	Material	Hom. Mat. #	% Asb.	Ft ² /L.F.	Location	Condition: Code & Comments	Friable Yes/No
M	TRANSITE PANELS		ASSUMED	UNDETERMINED	EXTERIOR	(1) (4) (12/05/01, 5/14/02 Same)	N

School: Chapman Elementary School

Building: F

Material Class	Material	Hom. Mat. #	% Asb.	Ft ² /L.F.	Location	Condition: Code & Comments	Friable Yes/No
M	9" VFT		1-5%	UNDETERMINED	ROOM 3 (CLASSROOM 66)	(1) (4) (12/05/01, 5/14/02 Same)	N
M	9" VFT		1-5%	UNDETERMINED	ROOM 1 (CLASSROOMS 5 & 7)	(1) (4) ↓ ↓	N
M	TRANSITE PANELS		ASSUMED	UNDETERMINED	EXTERIOR	(1) (4) ↓ ↓	N

CONDITION CODE

General Condition: (1) Good (2) Damaged (3) Significantly Damaged (25% or more)
 Change in Condition: (4) No (5) Yes (If Yes, explain under comments)
 Abated: (6) Repaired (7) Removed (8) Encapsulated (9) Enclosed (10) Isolated & Restricted
 Miscellaneous: (11) Inaccessible, no inspection data (12) Other (Explain under comments) (13) Non-Asbestos/Not Inspected

CONSULT ORIGINAL AND SUPPLEMENTARY INSPECTION REPORTS FOR MATERIALS WITH TRACE AMOUNTS OF ASBESTOS

**SIX MONTHS ASBESTOS SURVEILLANCE
HOMOGENEOUS ASBM RECORDS**

Date of Inspection: 03/14/2002

District: Chico Unified School District

Inspector: Robert Peters

School: Chapman Elementary School

Building: G

Material Class	Material	Homo. Mat. #	% Asb.	F ² /L.F.	Location	Condition: Code & Comments	Friable Yes/No
T	MUD JOINT		1-5%	UNDETERMINED	ROOMS 1-4	(1) (4) (12/05/01, 5/14/02 Same)	N
M	TRANSITE PANELS		ASSUMED	UNDETERMINED	ROOMS 1-4	(11) COULD NOT FIND.	N

CONDITION CODE

General Condition: (1) Good (2) Damaged (3) Significantly Damaged (25% or more)
Change in Condition: (4) No (5) Yes (If Yes, explain under comments)
Abated: (6) Repaired (7) Removed (8) Encapsulated (9) Enclosed (10) Isolated & Restricted
Miscellaneous: (11) Inaccessible, no inspection data (12) Other (Explain under comments) (13) Non-Asbestos/Not Inspected

CONSULT ORIGINAL AND SUPPLEMENTARY INSPECTION REPORTS FOR MATERIALS WITH TRACE AMOUNTS OF ASBESTOS



Bulk Asbestos Analysis

(EPA Method 600/R-93-116, Visual Area Estimation)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B045603
Date Received: 12/05/02
Date Analyzed: 12/06/02
Date Printed: 12/06/02
First Reported: 12/06/02

Job ID / Site: Chapman Elementary School, Main Hallway

FASI Job ID: 2921-57


Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
MH-1	10199615						
		Layer: Black Tar					ND
		Layer: Black Felt					ND
		Layer: Black Tar					ND
		Layer: Black Felt					ND
		Layer: Black Tar					ND
		Layer: Black Felt					ND
		Layer: Black Tar					ND
		Layer: Black Felt					ND

Total Composite Values of Fibrous Components: **Asbestos:(ND)**
 Cellulose (Trace%) Fibrous Glass (45%)
 Comment: Bulk complex sample. Collected on 12/03/2002

MH-2	10199616						
		Layer: Black Tar					ND
		Layer: Black Felt					ND
		Layer: Black Tar					ND
		Layer: Black Felt					ND
		Layer: Black Tar					ND
		Layer: Black Felt					ND
		Layer: Black Tar					ND
		Layer: Black Felt					ND

Total Composite Values of Fibrous Components: **Asbestos:(ND)**
 Cellulose (Trace%) Fibrous Glass (45%)
 Comment: Bulk complex sample. Collected on 12/03/2002

*C: Mary
Kip
Bob m
Rob
Aler
Bindus (3)*





Bulk Asbestos Analysis

(EPA Method 600/R-93-116, Visual Area Estimation)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B045603
Date Received: 12/05/02
Date Analyzed: 12/06/02
Date Printed: 12/06/02
First Reported: 12/06/02

Job ID / Site: Chapman Elementary School, Main Hallway

FASI Job ID: 2921-57

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
MH-5	10199619						
Layer: Black Tar							ND
Layer: Black Felt							ND
Layer: Black Tar							ND
Layer: Black Felt							ND
Layer: Black Tar							ND
Layer: Black Felt							ND
Layer: Black Tar							ND
Layer: Black Felt							ND

Total Composite Values of Fibrous Components: Asbestos:(ND)

Trace (Trace%) Fibrous Glass (45%)

Comment: Bulk complex sample. Collected on 12/03/2002

James Flores, Laboratory Supervisor, Hayward Laboratory

Note: Limit of Quantification ('LOQ') = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.

Analytical results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) named on the report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written request from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified. All samples were received in acceptable condition unless otherwise noted.



IT NAME & ADDRESS:

2921-57 Chico Unified School District
2455 Carmichael Drive
Chico, CA 95928

PHONE: (916) 891-
FAX: (916) 891-3190

DATE:

Circle the Method and
Turn Around Time

Results Needed

24 hr/12hr/24hr/48hr/Ext

PLM: Standard / Point Count

Gravimetry Prep

CONTACT: ROB PETERS

TEM: QUAL. / QUANT. / WATER

P.O.#

JOB #

AA/Flame AA/Furnace ICP

SITE: CHAPMAN

METALS:

SAMPLE NUMBER	DATE COLLECTED	SAMPLE LOCATION/DESCRIPTION
MH-1	12/3/02	MAIN HALLWAY
MH-2	↓	MAIN HALLWAY
MH-3		MAIN HALLWAY
MH-4		MAIN HALLWAY
MH-5		MAIN HALLWAY

Sampled by: ROB PETERS

Date: 12/3/02 Time: 1:10 PM

Relinquished by:

Received By: Melissa Gomez

Date/Time:

Date/Time: 12/5/02
Sealed Condition (circle one) YES / NO

Inquished by:

Received By:

Date/Time:

Date/Time:
Sealed Condition (circle one) YES / NO

Maintenance and Operations
2455 Carmichael Drive
Chico, CA 95928
Phone: (530) 891-3195
Fax: (530) 891-3190

Chico Unified School District

December 4, 2002

Forensic Analytical Specialties, Inc.
3777 Depot Road, Suite 409
Hayward, CA 94545

Re: Chapman Elementary School

To Whom It May Concern:

Please test the enclosed samples from the Chapman Elementary School Main Hallway for asbestos. We would like a 24-hour turnaround on the samples. Please fax the results to us as soon as soon as they are available. Our fax number is (530) 891-3190.

Site Sampled:	Chapman Elementary School
Location:	Main Hallway
Date Sampled:	December 3, 2002
Number of Samples:	Five (5)

Thank you for your prompt response to this request.

Sincerely,



Rob Peters
Maintenance/Operations Supervisor

RP:dlg
Enclosures



Forensic Analytical
Analytical Report

Preliminary FAX

Bulk Asbestos Analysis

(EPA Method 600/R-93-116)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B045603
Date Received: 12/05/02
Date Analyzed: 12/06/02
Date Printed: 12/06/02

Job ID / Site: Chapman Elementary School, Main Hallway

FA SI Job ID: 2921-57

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
MH-3	10199617						
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				

Total Composite Values of Fibrous Components: Asbestos:(ND)

Cellulose (Trace%) Fibrous Glass (45%)

Comment: Bulk complex sample.

MH-4 10199618

Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND

Total Composite Values of Fibrous Components: Asbestos:(ND)

Cellulose (Trace%) Fibrous Glass (45%)

Comment: Bulk complex sample.



Forensic Analytical
Analytical Report

Preliminary FAX

Bulk Asbestos Analysis

(EPA Method 600/R-93-116)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B045603
Date Received: 12/05/02
Date Analyzed: 12/06/02
Date Printed: 12/06/02

Job ID / Site: Chapman Elementary School, Main Hallway

FASI Job ID: 2921-57

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
MH-5	10199619						
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				

Total Composite Values of Fibrous Components: Asbestos:(ND)

Cellulose (Trace%) Fibrous Glass (45%)

Comment: Bulk complex sample.

James Flores, Laboratory Supervisor, Hayward Laboratory

Note: Limit of Quantification (LOQ) = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.

All analytical results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) on such report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written consent from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified. All samples were received in acceptable condition unless otherwise noted.



Forensic Analytical

BULK SAMPLE REQUEST FORM

IT NAME & ADDRESS: 2921 ⁻⁵⁷ Chico Unified School District 2455 Carmichael Drive Chico, CA 95928	PHONE: (916) 891- FAX: (916) 891-3190	DATE:
	Circle the Method and Turn Around Time 24 hr/12hr/24hr/48hr/Ext	Results Needed:
	PLM: <u>Standard</u> / Point Count	Gravimetry Prep
CONTACT: ROB PETERS.		TEM: QUAL / QUANT. / WATER
P.O.#	JOB #	AA/Flame AA/Furnace ICP
SITE: CHAPMAN		METALS:

SAMPLE NUMBER	DATE COLLECTED	SAMPLE LOCATION/DESCRIPTION
MH-1	12/3/02	MAIN HALLWAY
MH-2	↓	MAIN HALLWAY
MH-3		MAIN HALLWAY
MH-4		MAIN HALLWAY
MH-5		MAIN HALLWAY

Sampled by: ROB PETERS	Date: 12/3/02 Time: 1:10 PM
Reinquished by:	Received By: Melissa Cohen
Date/Time:	Date/Time: 12/5/02
Inquished by:	Received By:
Date/Time:	Date/Time:
	Sealed Condition (circle one) YES / NO
	Sealed Condition (circle one) YES / NO

Maintenance and Operations
2455 Carmichael Drive
Chico, CA 95928
Phone: (530) 891-3195
Fax: (530) 891-3190

Chico Unified School District

December 4, 2002

Forensic Analytical Specialties, Inc.
3777 Depot Road, Suite 409
Hayward, CA 94545

Re: Chapman Elementary School


To Whom It May Concern:

Please test the enclosed samples from the Chapman Elementary School Main Hallway for asbestos. We would like a 24-hour turnaround on the samples. Please fax the results to us as soon as soon as they are available. Our fax number is (530) 891-3190.

Site Sampled:	Chapman Elementary School
Location:	Main Hallway
Date Sampled:	December 3, 2002
Number of Samples:	Five (5)

Thank you for your prompt response to this request.

Sincerely,



Rob Peters
Maintenance/Operations Supervisor

RP:djg
Enclosures

Maintenance and Operations
2455 Carmichael Drive
Chico, CA 95928
Phone: (530) 891-3095
Fax: (530) 891-3190

Chico Unified School District

April 10, 2002

Forensic Analytical Specialties, Inc.
3777 Depot Road, Suite 409
Hayward, CA 94545

Re: District Office – Large Conference Room
Chapman Elementary School – Room 6 Storage

To Whom It May Concern:

Please test the enclosed roof sample from the District Office Large Conference Room and the ceiling plaster sample from Chapman Elementary School Room 6 Storage for asbestos. We would like a 24-hour turnaround on the samples. Please fax the results to us as soon as they are available. Our fax number is (530) 891-3190.


Site Sampled: District Office
Location: Large Conference Room Roof, under the shakes
Date Sampled: April 10, 2002
Number of Samples: One (1)

Site Sampled: Chapman Elementary School
Location: Plaster Ceiling in Unit A, Room 6 Storage
Date Sampled: April 10, 2002
Number of Samples: One (1)

Samples Taken by: Rob Peters

Thank you for your prompt response to this request.

Sincerely,



Rob Peters
Maintenance/Operations Supervisor

RP:dlg
Enclosures



Forensic Analytical
Analytical Report

Preliminary FAX

Bulk Asbestos Analysis

(EPA Method 600/R-93-116)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B038472
Date Received: 04/11/02
Date Analyzed: 04/12/02
Date Printed: 04/12/02

Job ID / Site: JOB: Chapman E.S.

FASI Job ID: 2921-38

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
A-6	10151615						
		Layer: Beige Plaster		ND			
		Layer: Paint		ND			

Total Composite Values of Fibrous Components: **Asbestos:(ND)**
Cellulose (Trace%)

James Flores, Laboratory Supervisor, Hayward Laboratory

Note: Limit of Quantification ('LOQ') = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.

tical results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) on such report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written st from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified.



Bulk Asbestos Analysis

(EPA Method 600/R-93-116, Visual Area Estimation)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928


Client ID: 2921
Report Number: B038472
Date Received: 04/11/02
Date Analyzed: 04/12/02
Date Printed: 04/12/02
First Reported: 04/12/02

Job ID / Site: JOB: Chapman E.S.

FASI Job ID: 2921-38

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
A-6	10151615						
Layer: Beige Plaster					ND		
Layer: Paint					ND		

Total Composite Values of Fibrous Components: **Asbestos:(ND)**
Cellulose (Trace%)
Comment: Collected on 04/10/2002



Jim Flores

James Flores, Laboratory Supervisor, Hayward Laboratory

Note: Limit of Quantification ('LOQ') = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.

All results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) named on report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written request from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified.

Forensic Analytical

San Francisco • Los Angeles • Minneapolis / St. Paul

