

Homogeneous Materials Record

School Dist: Chico USD
Date Inspected: 04/16/92

School: FAIRVIEW

BUILDING: A

Material	Homog. Mat. #	Locations	% Asb	Footage	Friable? Y or N
ACT	9	RMS 1 AND 2	00-00	1920 S	N
9" VFTs	10	RM 1	01-05	960 S	N
9" VFTs	10	RM 2	01-05	960 S	N

Inspected By: MIKE SHARP

These Reports should be placed in your AHERA file. Do not throw away old HMRs.

Homogeneous Materials Record

School Dist: Chico USD
Date Inspected: 04/16/92

School: FAIRVIEW

BUILDING: B

Material	Homog. Mat. #	Locations	% Asb	Footage Y or N	Friable?
ACT	9	RMS 1,2,3,4,6 & 7	00-00	4600 S	N
9" VFTs	10	ALL CLS RMS	01-05	4300 S	N
9" VFTs	10	RM 6	01-05	300 S	N

Inspected By: MIKE SHARP

These Reports should be placed in your AHERA file. Do not throw away old HMRs.

Homogeneous Materials Record

School Dist: **Chico USD**

School: **FAIRVIEW**

Date Inspected: **04/16/92**

BUILDING: **C**

Material	Homog. Mat. #	Locations	% Asb	Footage Y or N	Friable?
NONE LISTED	0	CHECK DRYWALL & VFT	99-99 ASSUMED	0	
FCP	12	RM 1	00-00	960 S	N

Inspected By: **MIKE SHARP**

These Reports should be placed in your AHERA file. Do not throw away old HMRs.

Homogeneous Materials Record

School Dist: Chico USD

School: FAIRVIEW

Date Inspected: 04/16/92

BUILDING: MPR

Material	Homog. Mat. #	Locations	% Asb	Footage	Friable? Y or N
MUD JNT	1	KITCHEN	65-70	10	N
9" VFTs	2	ENTRY	01-05	90 S	N
9" VFTs	2	FOOD STRG (ART OFF)	01-05	145 S	N
9" VFTs	2	MPR	01-05	2600 S	N
9" VFTs	2	S-STORAGE	01-05	104 S	N
CEILING MATRL	3	COLD STORAGE	00-00	75 S	N
WALL PLASTER	4	ALL ROOMS	00-01 TRACE	6500 S	N
C'LING PLASTER	5	MPR	01-05	2600 S	N
BLR INSL	7	BLR RM	75-80	150 S	N
MUD JNT	8	BLR RM	35-40	32 L	Y
TRANSITE PIPE	99	BLR RM (TWO PIPES)	99-99 ASSUMED	25 L	N

Inspected By: MIKE SHARP

These Reports should be placed in your AHERA file. Do not throw away old

Homogeneuos Materials Record

School Dist: Chico USD

School: FAIRVIEW

Date Inspected: 04/16/92

BUILDING: MPR

Material	Homog. Mat. #	Locations	% Asb	Friable? Footage Y or N

HMRs.				

Homogeneous Materials Record

School Dist: **Chico USD**
Date Inspected: **04/16/92**

School: **FAIRVIEW**

BUILDING: **A**

Material	Homog. Mat. #	Locations	% Asb	Footage	Friable? Y or N
DRYWALL	75	OFFICE WALLS	00-01 TRACE	400 S	N
DRYWALL	75	RRs AND CUST RMs	00-01 TRACE	1000 S	N

Inspected By: **MIKE SHARP**

These Reports should be placed in your AHERA file. Do not throw away old HMRs.

Homogeneous Materials Record

School Dist: Chico USD

School: FAIRVIEW

Date Inspected: 04/16/92

BUILDING: GREENHOUSE

Material	Homog. Mat. #	Locations	% Asb	Footage Y or N	Friable?
DRYWALL	75	GREENHOUSE	00-01 TRACE	600 S	N

Inspected By: MIKE SHARP

These Reports should be placed in your AHERA file. Do not throw away old HMRs.

Homogeneous Materials Record

School Dist: **Chico USD**

School: **FAIRVIEW**

Date Inspected: **04/16/92**

BUILDING: **A**

Material	Homog. Mat. #	Locations	% Asb	Footage	Friable? Y or N
ACT	9	RMS 1 AND 2	00-00	1920 S	N
9" VFTs	10	RM 1	01-05	960 S	N
9" VFTs	10	RM 2	01-05	960 S	N

Inspected By: **MIKE SHARP**

These Reports should be placed in your AHERA file. Do not throw away old HMRs.

Homogeneous Materials Record

School Dist: **Chico USD**
Date Inspected: **04/16/92**

School: **FAIRVIEW**

BUILDING: **B**

Material	Homog. Mat. #	Locations	% Asb	Footage	Friable? Y or N
ACT	9	RMS 1,2,3,4,6 & 7	00-00	4600 S	N
9" VFTs	10	ALL CLS RMS	01-05	4300 S	N
9" VFTs	10	RM 6	01-05	300 S	N

Inspected By: **MIKE SHARP**

These Reports should be placed in your AHERA file. Do not throw away old HMRs.

Homogeneous Materials Record

School Dist: Chico USD

School: FAIRVIEW

Date Inspected: 04/16/92

BUILDING: C

Material	Homog. Mat. #	Locations	% Asb	Footage Y or N	Friable?
NONE LISTED	0	CHECK DRYWALL & VFT	99-99 ASSUMED	0	
FCP	12	RM 1	00-00	960 S	N

Inspected By: MIKE SHARP

These Reports should be placed in your AHERA file. Do not throw away old HMRS.

Homogeneous Materials Record

School Dist: Chico USD

School: FAIRVIEW

Date Inspected: 04/16/92

BUILDING: MPR

Material	Homog. Mat. #	Locations	% Asb	Footage	Friable? Y or N
MUD JNT	1	KITCHEN	65-70	10	N
9" VFTs	2	ENTRY	01-05	90 S	N
9" VFTs	2	FOOD STRG (ART OFF)	01-05	145 S	N
9" VFTs	2	MPR	01-05	2600 S	N
9" VFTs	2	S-STORAGE	01-05	104 S	N
CEILING MATRL	3	COLD STORAGE	00-00	75 S	N
WALL PLASTER	4	ALL ROOMS	00-01 TRACE	6500 S	N
C'LING PLASTER	5	MPR	01-05	2600 S	N
BLR INSL	7	BLR RM	75-80	150 S	N
MUD JNT	8	BLR RM	35-40	32 L	Y
TRANSITE PIPE	99	BLR RM (TWO PIPES)	99-99 ASSUMED	25 L	N

Inspected By: MIKE SHARP

These Reports should be placed in your AHERA file. Do not throw away old

Homogeneuos Materials Record

School Dist: Chico USD

School: FAIRVIEW

Date Inspected: 04/16/92

BUILDING: MPR

Material	Homog. Mat. #	Locations	% Asb	Friable? Footage Y or N

HMRS.				

Hazard Management Services, Inc. Bulk Sample Analysis Request Form

AHERA THREE YEAR REINSPECTION SAMPLES

Please Send Results To: P.O. Box 576848 Modesto, CA 95357-6848

Samples Collected by: Michael Sharp on 04/16/92

Client: Chico Unified S.D. Site: Fairview

Turn Around Time: Extended, Results Needed By April 30th, if possible.

Sample Number	Material	Location
HMS-CUSD-FRV -75A	Drywall	Principal's Office
	Result: None Detected	
HMS-CUSD-FRV -75B	Drywall	Back Offices of Admin.
	Result: Trace amount of asbestos in skim coat only.	
HMS-CUSD-FRV -75C	Drywall	Unit B playpen room at door jam.
	Result: Trace amount of asbestos in skim coat only.	



Bulk Material Analysis

Client:

Hazard Management Services, Inc.
Modesto Location
P.O. Box 576848
Modesto, CA 95357-6848

Client Number: 1146
Report Number: 177336
Date Received: 04/21/92

Lab Number: 19220551
Sample Number: HMS-CUSD-FRV-75A
P.O. Num:
Job ID: Chico Unified School District
Site: Fairview

Date Collected: 04/16/92

Location: Principal's office, drywall.

Gross Description: White fibrous powder with paint and fibrous backing.

Comments:

Microscopic Description

TOTAL ASBESTOS PRESENT:

Chrysotile
Amosite

Non-Det. %

Non-Det. %

%

%

Non-Det. %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose
Fibrous Glass

10-15

1-5

%

%

%

%

15-20 %

NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

80-85 %

Janis Teichman

Janis Teichman, Director of Laboratory Services, Hayward Laboratory

Analytical Method: 40 CFR 763, Subpart F, Appendix A (ARMA)

See Reverse for Explanation of Terms and Reporting Practices



Forensic Analytical
Analytical Report

Bulk Material Analysis

Client:

Hazard Management Services, Inc.
Modesto Location
P.O. Box 576848
Modesto, CA 95357-6848

Client Number: 1146
Report Number: 177336
Date Received: 04/21/92

Lab Number: 19220552
Sample Number: HMS-CUSD-PRV-75B
P.O. Num:
Job ID: Chico Unified School District
Site: Fairview

Date Collected: 04/16/92

Location: Back offices of admin., drywall.

Gross Description: White fibrous powder with paint, fibrous backing and skim coat.

Comments: Asbestos in skim coat (trace). Composite reported.

Microscopic Description

TOTAL ASBESTOS PRESENT:

Chrysotile
Amosite

Trace %
Non-Det. %

Trace %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose
Fibrous Glass

1-5 %
1-5 %

5-10 %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

90-95 %

Janis Teichman

Janis Teichman, Director of Laboratory Services, Hayward Laboratory

Analytical methods: 40 CFR 163, Subpart F, Appendix A (AHERA)

See Reverse for Explanation of Terms and Reporting Practices

San Francisco Office: 3777 Depot Road, Suite 409, Hayward, California 94545 • Telephone: 510/887-8828 800/827-FASI Fax: 510/887-4218
Los Angeles Office: 19443 Laurel Park Road, Suite 101, Rancho Dominguez, California 90220 • Telephone: 310/763-2374 Fax: 310/763-8684



Forensic Analytical
Analytical Report

Bulk Material Analysis

Client:

Hazard Management Services, Inc.
Modesto Location
P.O. Box 576848
Modesto, CA 95357-6848

Client Number: 1146
Report Number: 177336
Date Received: 04/21/92

Lab Number: 19220553
Sample Number: HMS-CUSD-FRV-75C
P.O. Num:
Job ID: Chico Unified School District
Site: Fairview

Date Collected: 04/16/92

Location: Unit B playpen room at door jam, drywall.

Gross Description: White fibrous powder with paint, fibrous backing and skim coat.

Comments: Asbestos in skim coat (trace). Composite reported.

Microscopic Description

TOTAL ASBESTOS PRESENT:

Chrysotile
Amosite

Trace %
Non-Det. %
%
%

Trace %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose
Fibrous Glass

10-15 %
1-5 %
%
%

15-20 %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

80-85 %

Janis Peiskman


Janis Peiskman, Director of Laboratory Services, Hayward Laboratory

Analytical method: 40 CFR 763, Subpart F, Appendix A (AHEHA)

See Reverse for Explanation of Terms and Reporting Practices

San Francisco Office: 3777 Depot Road, Suite 409, Hayward, California 94545 • Telephone: 510/887-8828 800/827-FASL Fax: 510/667-4218
Los Angeles Office: 14443 Laurel Park Road, Suite 101, Rancho Dominguez, California 90220 • Telephone: 310/763-2374 Fax: 310/763-8684

United States Department of Commerce
National Institute of Standards and Technology



Certificate of Accreditation

FORENSIC ANALYTICAL SPECIALTIES, INC.
HAYWARD, CA

*is recognized under the National Voluntary Laboratory Accreditation Program
for satisfactory compliance with criteria established in Title 15, Part 7 Code of Federal Regulations.
Accreditation is awarded for specific services, listed on the Scope of Accreditation, for:*

BULK ASBESTOS FIBER ANALYSIS

July 1, 1993

Effective until



Albert D. Phalen
For the National Institute of Standards and Technology

DISTRICT Chicago SCHOOL Felicitas ADDRESS _____

[illegible]

DISTRICT Unico Unified SCHOOL Farview

ADDRESS

[illegible]

DISTRICT Chase SCHOOL Franklin

[illegible]

DISTRICT Unico Unified SCHOOL Fairview 3

ADDRESS

[illegible]

DISTRICT	UNION UNIFIED	SCHOOL	Fairview 3
----------	---------------	--------	------------

MAT. CLASS.		MATERIAL		HOMOG. SAMPLE		LOCATION		% ASBESTOS		FOOTAGE FT ² or LF		FRIABLE YES NO	
BLDG.	TSE	BIR	INS	MAT.#	NUMBER			ASBESTOS		FOOTAGE		FRIABLE	
MPR	TSE	BIR	INS	07	07	Boiler Room		75-80		150 ft		X	
MPR	MISC	Transite	pipe	99	NS	Boiler Room (Two pipes)		Assumed		25' of 12"		X	
MPR	TSE	MAV	INT	08	08	Boiler Room		35-40		32 JNTS		X	
PORT						NO ACBM							

HMS, INC.
HAZARD MANAGEMENT SERVICES, INC.

CHICO UNIFIED SCHOOL DISTRICT
FAIR VIEW HIGH SCHOOL
AHERA THREE-YEAR REINSPECTION SUMMARY
APRIL, 1992

Attached you will find a computer print-out of your original "Homogeneous Materials Record Sheets". You will find these sheets easier to read than the original copies. If additional samples were collected at this site, the results are listed at the end of the new "homogeneous" sheets. A comment on drywall sampling and lab accreditation sheets are added as appropriate.

At this site all previously or currently identified asbestos-containing materials were in good condition, i.e., non-friable.

We have given you a new index to insert into your management plan to account for new sections VIII and IX. We have added section VIII in which you should include results of your six-month inspections. We have also included a sheet on drywall sampling with recommendations on handling drywall. We also want to remind you that new buildings or portables must either be inspected or exempted by letter by your architect or builder.

AHERA THREE YEAR REINSPECTION

School Dist: **Chico USD**
 Date Inspected: **04/16/92**

School: **FAIRVIEW**

BUILDING: **A**

Material	Homog. Mat. #	Locations	% Asb	Footage	Codes
9" VFTs	10	RM 1	01-05	960 S	1-4
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? NO Abated? NO Comments:					
9" VFTs	10	RM 2	01-05	960 S	1-4
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? NO Abated? NO Comments:					
DRYWALL	75	OFFICE WALLS	00-01 (TRACE)	400 S	1-4
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? NO Abated? NO Comments:TRACE ASBESTOS IN SKIM COAT ONLY.					
DRYWALL	75	RRs AND CUST RMs	00-01 (TRACE)	1000 S	1-4
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? NO Abated? NO Comments:TRACE ASBESTOS IN SKIM COAT ONLY.					

Codes:

General Condition: (1) Good (2) Damaged (3) Sig. Damaged
 Change in Condition: (N or 4) No (Y) Yes (Please explain)
 Abated: (R) Repaired (M) Removed (E) Enclsd
 (I) Isolated and Restricted

Inspected By: **MIKE SHARP**

These Reports should be placed in your AHERA file. Do not throw away old HMRs.

AHERA THREE YEAR REINSPECTION

School Dist: **Chico USD**
Date Inspected: **04/16/92**

School: **FAIRVIEW**

BUILDING: **B**

Material	Homog. Mat. #	Locations	% Asb	Footage	Codes
-----------------	--------------------------	------------------	--------------	----------------	--------------

9" VFTs	10	ALL CLS RMS	01-05	4300 S	1-4
---------	----	-------------	-------	--------	-----

3 Year Inspection Notes:

Condition of Material: GOOD

Change in Condition? NO **Abated?** NO

Comments:

9" VFTs	10	RM 6	01-05	300 S	1-4
---------	----	------	-------	-------	-----

3 Year Inspection Notes:

Condition of Material: GOOD

Change in Condition? NO **Abated?** NO

Comments:

Codes:

General Condition: (1) Good (2) Damaged (3) Sig. Damaged
Change in Condition: (N or 4) No (Y) Yes (Please explain)
Abated: (R) Repaired (M) Removed (E) Enclsd
(I) Isolated and Restricted

Inspected By: MIKE SHARP

These Reports should be placed in your AHERA file. Do not throw away old HMRS.

AHERA THREE YEAR REINSPECTION

School Dist: Chico USD

School: FAIRVIEW

Date Inspected: 04/16/92

BUILDING: C

Material	Homog. Mat. #	Locations	% Asb	Footage	Codes
NONE LISTED	0	CHECK DRYWALL & VFT	01-99 (ASSUMED)	0	0-
3 Year Inspection Notes:					
Condition of Material: NO SURVEILLANCE DATA					
Change in Condition? NO Abated? NO					
Comments:					

Codes:

General Condition: (1) Good (2) Damaged (3) Sig. Damaged
Change in Condition: (N or 4) No (Y) Yes (Please explain)
Abated: (R) Repaired (M) Removed (E) Enclsd
(I) Isolated and Restricted

Inspected By: MIKE SHARP

These Reports should be placed in your AHERA file. Do not throw away old HMRs.

AHERA THREE YEAR REINSPECTION

School Dist: **Chico USD**
Date Inspected: **04/16/92**

School: **FAIRVIEW**

BUILDING: **GREENHOUSE**

Material	Homog. Mat. #	Locations	% Asb	Footage	Codes
DRYWALL	75	GREENHOUSE	00-01 (TRACE)	600 S	1-4

3 Year Inspection Notes:
Condition of Material: GOOD
Change in Condition? NO **Abated?** NO
Comments: TRACE ASBESTOS IN SKIM COAT ONLY.

Codes:

General Condition: (1) Good (2) Damaged (3) Sig. Damaged
Change in Condition: (N or 4) No (Y) Yes (Please explain)
Abated: (R) Repaired (M) Removed (E) Enclsd
(I) Isolated and Restricted

Inspected By: MIKE SHARP

These Reports should be placed in your AHERA file. Do not throw away old HMRS.

AHERA THREE YEAR REINSPECTION

School Dist: **Chico USD**
 Date Inspected: **04/16/92**

School: **FAIRVIEW**

BUILDING: MPR

Material	Homog. Mat. #	Locations	% Asb	Footage	Codes
MUD JNT	1	KITCHEN	65-70	10	0-Y
3 Year Inspection Notes: Condition of Material: Change in Condition? YES Abated? REMOVED Comments:					
9" VFTs	2	ENTRY	01-05	90 S	1-4
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? NO Abated? NO Comments:					
9" VFTs	2	FOOD STRG (ART OFF)	01-05	145 S	1-4
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? NO Abated? NO Comments:					
9" VFTs	2	MPR	01-05	2600 S	1-4
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? NO Abated? NO Comments:					
9" VFTs	2	S-STORAGE	01-05	104 S	1-4
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? NO Abated? NO Comments:					
C'LING PLASTER	5	MPR	01-05	2600 S	2-5
3 Year Inspection Notes: Condition of Material: DAMAGED Change in Condition? YES Abated? NO Comments: Many water stains. Material is not yet friable, though.					

AHERA THREE YEAR REINSPECTION

School Dist: **Chico USD**
 Date Inspected: **04/16/92**

School: **FAIRVIEW**

BUILDING: **MPR**

Material	Homog. Mat. #	Locations	% Asb	Footage	Codes
BLR INSL	7	BLR RM	75-80	150 S	1-4
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? NO Abated? NO Comments:					
MUD JNT	8	BLR RM	35-40	32 L	1-5
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? YES Abated? REPAIRED Comments:					
TRANSITE PIPE	99	BLR RM (TWO PIPES)	01-99 (ASSUMED)	25 L	1-4
3 Year Inspection Notes: Condition of Material: GOOD Change in Condition? NO Abated? NO Comments:					

Codes:

General Condition: (1) Good (2) Damaged (3) Sig. Damaged
Change in Condition: (N or 4) No (Y) Yes (Please explain)
Abated: (R) Repaired (M) Removed (E) Enclsd
 (I) Isolated and Restricted

Inspected By: MIKE SHARP

These Reports should be placed in your AHERA file. Do not throw away old HMRS.

UNIVERSITY OF CALIFORNIA BERKELEY UNIVERSITY EXTENSION

This is to certify that

MICHAEL C. SHARP

has attended the

AHERA Refresher Course for Asbestos Inspectors and
Management Planners
November 26, 1991

Certificate number:

1428

Valid until: November 26, 1992



Deloral DA.
Chair
Programs in Environmental Hazard
Management

UNIVERSITY OF CALIFORNIA BERKELEY UNIVERSITY EXTENSION

This is to certify that

MICHAEL C. SHARP

has attended the

AHERA Refresher Course for Asbestos Abatement Project Designers
October 22, 1991

Certificate number:

Valid until: October 22, 1992



Deloral DA.
Chair
Programs in Environmental Hazard
Management

SIX MONTH SURVEILLANCE HOMOGENEOUS ACBM RECORDS

Date of Inspection: 11-24-2003

District: Chico Unified School District

Inspector: Robert Baughman

School: Fairview High School

Building: A

Material Class	Material	Homo. Mat. #	% Asb.	FT ² /L.F.	Location	Condition: Code & Comments	Friable Yes/No
M	9" VFT BEIGE	10	1-5%	1,920 S	ROOMS 1 & 2	(1) (4) SAME 11/24/03	N
M	DRYWALL	75	TRACE	1,400 S	OFFICE WALLS, RESTROOMS, & CUSTODIAN ROOM	(1) (4) SAME 11/24/03	N

School: Fairview High School

Building: B

Material Class	Material	Homo. Mat. #	% Asb.	FT ² /L.F.	Location	Condition: Code & Comments	Friable Yes/No
M	9" VFT	10	1-5%	4,300 S	ALL CLASSROOMS & COUNSELING OFFICES	(1) (4) SAME 11/24/03	N
M	DRYWALL	98	ASSUMED	600 S	BOYS & GIRL'S RESTROOMS	(1) SAME 11/24/03	N

CONDITION CODE

General Condition: (1) Good (2) Damaged (3) Significantly Damaged (25% or more)

Change in Condition: (4) No (5) Yes (If Yes, explain under comments)

Abated: (6) Repaired (7) Removed (8) Encapsulated (9) Enclosed (10) Isolated & Restricted

Miscellaneous: (11) Inaccessible, no inspection data (12) Other (Explain under comments) (13) Non-Asbestos/Not Inspected

CONSULT ORIGINAL AND SUPPLEMENTARY INSPECTION REPORTS FOR MATERIALS WITH TRACE AMOUNTS OF ASBESTOS

SIX-MONTH SURVEILLANCE

Page 1 of 1

DISTRICT Chico Unified School District

DATE December 28, 1992

SCHOOL Fairview High School

INSPECTOR Michael Fender

BLDG. HOMOG. ASBESTOS MATERIAL LOCATION CONDITION: CODE & COMMENTS

A	9" VFT	1-5	Rooms 1 & 2 (Beige)	(1) Good (4)
B	9" VFT	1-5	Rooms 4, 5, 3, 2	(1) Good (4)
MPR	Mud Jnt	65-70	Kitchen	(5) (7)
MPR	9" VFT	1-5	MPR (Green)	(2) (5) 6 tile damaged sw door
MPR	9" VFT	1-5	Food Storage, ARS Office	(1) Good (4)
MPR	9" VFT	1-5	S-storage & Food storage	(1) Good (4)
MPR	Ceill plas	1-5	MPR	(4)
MPR	Boil Insl	75-80	Boiler Room	(1) Good (4)
MPR	Tran pipe	Assumed	Boiler Room	(1) Good (4)
MPR	Mud Jnt	35-40	Boiler Room	(6) (4)

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)

CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)

ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTED

MISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)



Bulk Material Analysis

Client:

Hazard Management Services, Inc.
Modesto Location
P.O. Box 576848
Modesto, CA 95357-6848

Client Number: 1146
Report Number: 177336
Date Received: 04/21/92

Lab Number: 19220552

Date Collected: 04/16/92

Sample Number: HMS-CUSD-FRV-75B

P.O. Num:

Job ID: Chico Unified School District

Site: ~~██████████~~

Location: Back offices of admin., drywall.

Gross Description: White fibrous powder with paint, fibrous backing and skim coat.

Comments: ~~Asbestos in skim coat (trace)~~. Composite reported.

Macroscopic Description

TOTAL ASBESTOS PRESENT:

Chrysotile
Amosite

Trace %
Non-Det. %
%
%

Trace %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose
Fibrous Glass

1-5 %
1-5 %
%
%

5-10 %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

90-95 %

Janis Teichman

Janis Teichman, Director of Laboratory Services, Hayward Laboratory

Analytical method: 40 CFR 763, Subpart F, Appendix A (AHERA)

See Reverse for Explanation of Terms and Reporting Practices

San Francisco Office: 3777 Depot Road, Suite 409, Hayward, California 94545 • Telephone: 510/887-8828 800/827-FASI Fax: 510/887-4218
Los Angeles Office: 19443 Laurel Park Road, Suite 101, Rancho Dominguez, California 90220 • Telephone: 310/763-2374 Fax: 310/763-8684



Bulk Material Analysis

Client:

Hazard Management Services, Inc.
Modesto Location
P.O. Box 576848
Modesto, CA 95357-6848

Client Number: 1146
Report Number: 177336
Date Received: 04/21/92

Lab Number: 19220553

Date Collected: 04/16/92

Sample Number: HMS-CUSD-FRV-75C

P.O. Num:

Job ID: Chico Unified School District

Site: Fairview

Location: Unit B playpen room at door jam, drywall.

Gross Description: White fibrous powder with paint, fibrous backing and skim coat.

Comments: Asbestos in skim coat (trace). Composite reported.

Microscopic Description

TOTAL ASBESTOS PRESENT:

Chrysotile
Amosite

Trace %
Non-Det. %
%
%

Trace %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose
Fibrous Glass

10-15 %
1-5 %
%
%

15-20 %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

80-85 %

Janis Feichman

Janis Feichman, Director of Laboratory Services, Hayward Laboratory

Analytical method: 40 CFR 763, Subpart F, Appendix A (AHERA)

See Reverse for Explanation of Terms and Reporting Practices

San Francisco Office: 1777 Depot Road, Suite 409, Hayward, California 94545 • Telephone: 510/887-8828 800/827-FASL Fax: 510/887-4218
Los Angeles Office: 19443 Laurel Park Road, Suite 101, Rancho Dominguez, California 90220 • Telephone: 310/763-2374 Fax: 310/763-8684



Forensic Analytical
Analytical Report

Bulk Material Analysis

Client:

Hazard Management Services, Inc.
Modesto Location
P.O. Box 576848
Modesto, CA 95357-6848

Client Number: 1146
Report Number: 177336
Date Received: 04/21/92

Lab Number: 19220551
Sample Number: HMS-CUSD-FRV-75A
P.O. Num:
Job ID: Chico Unified School District
Site: Fairview

Date Collected: 04/16/92

Location: Principal's office, drywall.

Gross Description: White fibrous powder with paint and fibrous backing.

Comments:

Microscopic Description

TOTAL ASBESTOS PRESENT:

Chrysotile
Amosite

Non-Det. %
Non-Det. %

Non-Det. %

%
%

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose
Fibrous Glass

10-15 %
1-5 %

15-20 %

%
%

NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

80-85 %

Janis Teichman

Janis Teichman, Director of Laboratory Services, Hayward Laboratory

Analytical method: 40 CFR 703, Subpart F, Appendix A (AHERA)

See Reverse for Explanation of Terms and Reporting Practices

San Francisco Office: 3777 Depot Road, Suite 409, Hayward, California 94545 • Telephone: 510/887-8828 800/827-FASL Fax: 510/887-4218
Los Angeles Office: 19441 Laurel Park Road, Suite 101, Rancho Dominguez, California 90220 • Telephone: 310/763-2474 Fax: 310/763-8684