



Forensic Analytical
Analytical Report

Preliminary FAX

Bulk Asbestos Analysis

(EPA Method 600/R-93-116)

Chico Unified School Dist
Rob Peters

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B017158
Date Received: 2/3/00
Date Analyzed: 02/04/00
Date Printed: 02/04/00

FASI Job ID: 2921-21

Job ID / Site: Chico Senior High School, Boy's Locker Room Roof

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
#1	10007730		ND				
Layer: Black Tar							
Layer: Black Felt		Chrysotile	65%				
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65%				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	5%				
Layer: Silver Paint							

Total Composite Values of Fibrous Components:

Asbestos:(24%)

Cellulose (20%) Fibrous Glass (10%)

Comment: Bulk complex sample.

#2	10007731		ND				
Layer: Black Tar							
Layer: Black Felt		Chrysotile	65%				
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65%				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	5%				
Layer: Silver Paint							

Total Composite Values of Fibrous Components:

Asbestos:(24%)

Cellulose (20%) Fibrous Glass (10%)

Comment: Bulk complex sample.

Note: Limit of Quantification (LOQ) = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.

Analytical results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) named on such report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written request from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified.



Forensic Analytical
Analytical Report

Preliminary FAX

Bulk Asbestos Analysis

(EPA Method 600/R-93-116)

Chico Unified School Dist
Rob Peters

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B017158
Date Received: 2/3/00
Date Analyzed: 02/04/00
Date Printed: 02/04/00

Job ID / Site: Chico Senior High School, Boy's Locker Room Roof

FAI Job ID: 2921-21

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
#3	10007732						
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65%				
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65%				
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65%				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Silver Paint		Chrysotile	5%				

Total Composite Values of Fibrous Components:

Asbestos:(35%)

Cellulose (20%) Fibrous Glass (10%)

Comment: Bulk complex sample.

Note: Limit of Quantification ('LOQ') = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.

Analytical results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) named on such report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written request from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified.

2921-21

Maintenance and Operations
2455 Carmichael Drive
Chico, CA 95928
Phone: (530) 891-3094
Fax: (530) 891-3190

Chico Unified School District

February 02, 2000

Forensic Analytical Specialties, Inc.
3777 Depot Road, Suite 409
Hayward, CA 94545

Re: Roof Samples

To Whom It May Concern:

Please test the enclosed roof samples for asbestos. Please fax the results to me. My fax number is (530) 891-3190.

Site Sampled:

Chico Senior High School

Boy's Locker Room Roof

Date Sampled:

February 02, 2000

Number of Samples:

Three

Sample #1:

Boy's Locker Room Roof (silver)

Sample #2:

Boy's Locker Room Roof (silver)

Sample #3:


Boy's Locker Room Roof (silver)

Samples Taken by:

Rob Peters

Thank you for your prompt response to this request.

Sincerely,



Rob Peters
Maintenance/Operations Supervisor

RP:dlg

Enclosures

AWD
2/9/00
102
(F)

Where STUDENTS are the FIRST priority

Note: Limit of Quantification (LOQ) = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'. Analytical results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) named on such report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written request from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified.



Forensic Analytical


Bulk Asbestos Analysis

(EPA Method 600/R-93-116, Visual Area Estimation)

San Francisco • Los Angeles • Minneapolis / St. Paul

Chico Unified School Dist
Rob Peters

2455 Carmichael Drive
Chico, CA 95928



Client ID: 2921
Report Number: B017158
Date Received: 02/03/00
Date Analyzed: 02/04/00
Date Printed: 02/04/00
First Reported: 02/04/00

Job ID / Site: Chico Senior High School, Boy's Locker Room Roof

FAJI Job ID: 2921-21

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Layer
#1	10007730						
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65 %				
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65 %				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Silver Paint		Chrysotile	5 %				

Total Composite Values of Fibrous Components: Asbestos:(24%) Cellulose (20%) Fibrous Glass (10%)
Comment: Bulk complex sample.

#2	10007731						
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65 %				
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65 %				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Silver Paint		Chrysotile	5 %				

Total Composite Values of Fibrous Components: Asbestos:(24%) Cellulose (20%) Fibrous Glass (10%)
Comment: Bulk complex sample.



Forensic Analytical

Bulk Asbestos Analysis

(EPA Method 600/R-93-116, Visual Area Estimation)

San Francisco • Los Angeles • Minneapolis / St. Paul

Chico Unified School Dist
Rob Peters

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B017158
Date Received: 02/03/00
Date Analyzed: 02/04/00
Date Printed: 02/04/00
First Reported: 02/04/00

Job ID / Site: Chico Senior High School, Boy's Locker Room Roof

FASI Job ID: 2921-21

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Layer
#3	10007732						
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65 %				
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65 %				
Layer: Black Tar			ND				
Layer: Black Felt		Chrysotile	65 %				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Silver Paint		Chrysotile	5 %				

Total Composite Values of Fibrous Components: Asbestos:(35%) Cellulose (20%) Fibrous Glass (10%)
 Sample: Bulk complex sample.

Mark Floyd, Laboratory Supervisor, Hayward Laboratory

Note: Limit of Quantification ('LOQ') = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.

Analytical results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) named on this report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written request from the client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified.

2921-21

Maintenance and Operations
2455 Carmichael Drive
Chico, CA 95928
Phone: (530) 891-3095
Fax: (530) 891-3190

Chico Unified School District

February 02, 2000

Forensic Analytical Specialties, Inc.
3777 Depot Road, Suite 409
Hayward, CA 94545

Re: Roof Samples

To Whom It May Concern:

Please test the enclosed roof samples for asbestos. Please fax the results to me. My fax number is (530) 891-3190.

Site Sampled:

Chico Senior High School

Boy's Locker Room Roof

Date Sampled:

February 02, 2000

Number of Samples:

Three

Sample #1:

Boy's Locker Room Roof (silver)

Sample #2:

Boy's Locker Room Roof (silver)

Sample #3:

Boy's Locker Room Roof (silver)

Samples Taken by:

Rob Peters

Thank you for your prompt response to this request.

Sincerely,



Rob Peters
Maintenance/Operations Supervisor

RP:dlg
Enclosures

Where STUDENTS are the FIRST priority

Handwritten notes:
2/2/00
102
(F)



Forensic Analytical
Analytical Report

Preliminary FAX

Bulk Asbestos Analysis

(EPA Method 600/R-93-116)

Chico Unified School Dist
Rob Peters

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B022205
Date Received: 08/10/00
Date Analyzed: 08/11/00
Date Printed: 08/11/00

Job ID / Site: Chico Sr./Jr. High School-Unit 900/K

FASI Job ID: 2921-25

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
---------------	------------	---------------	------------------	---------------	------------------	---------------	------------------

1	10041565						
	Layer: Beige Cementitious Material	Chrysotile	2%				
	Layer: Paint		ND				

Total Composite Values of Fibrous Components:	Asbestos:(2%)	Cellulose (2%)	Fibrous Glass (ND)
---	---------------	----------------	--------------------

2	10041566						
	Layer: Off-White Cementitious Material	Chrysotile	2%				
	Layer: Paint		ND				

Total Composite Values of Fibrous Components:	Asbestos:(2%)	Cellulose (ND)	Fibrous Glass (ND)
---	---------------	----------------	--------------------

8/11/00
Per Vanessa
Sample #1 = CSHS
Sample #2 = CSHS

Note: Limit of Quantification ('LOQ') = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.

Analytical results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) named on such report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written request from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified.

Maintenance and Operations
3455 Cornichard Drive
Chico, CA 95926
Phone: (530) 891-3098
Fax: (530) 891-3190

Chico Unified School District

August 9, 2000

Forensic Analytical Specialties, Inc.
3777 Depot Road, Suite 409
Hayward, CA 94545

Re: Chico Junior High School Unit K Window Putty and
Chico Senior High School Unit 900 Window Putty

To Whom It May Concern:

Please test the enclosed window putty samples from both Chico Junior and Chico Senior High Schools for asbestos and lead. Please fax the results to me as soon as they are available. My fax number is (530) 891-3190.


Site Sampled:	Chico Senior High School
Location:	Unit 900 Window Putty
Date Sampled:	August 9, 2000
Number of Samples:	One

Site Sampled:	Chico Junior High School
Location:	Unit K Window Putty
Date Sampled:	August 9, 2000
Number of Samples:	One

Samples Taken by: Rob Peters

Thank you for your prompt response to this request.

Sincerely,



Rob Peters
Maintenance/Operations Supervisor

RP:dlg
Enclosures

Received by
Christina Hsu
8/10/00 10:00 AM
Fed 10

Where STUDENTS are the FIRST priority

Note: Limit of Quantification ('LOQ') = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.

Analytical results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) named on such report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written request from client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified.

Maintenance and Operations
2455 Carmichael Drive
Chico, CA 95928
Phone: (530) 891-3095
Fax: (530) 891-3190

Chico Unified School District

August 9, 2000

Forensic Analytical Specialties, Inc.
3777 Depot Road, Suite 409
Hayward, CA 94545

2921-25

Re: Chico Junior High School Unit K Window Putty and
Chico Senior High School Unit 900 Window Putty

To Whom It May Concern:

Please test the enclosed window putty samples from both Chico Junior and Chico Senior High Schools for asbestos and lead. Please fax the results to me as soon as soon as they are available. My fax number is (530) 891-3190.


Site Sampled:	Chico Senior High School
Location:	Unit 900 Window Putty
Date Sampled:	August 9, 2000
Number of Samples:	One

Site Sampled:	Chico Junior High School
Location:	Unit K Window Putty
Date Sampled:	August 9, 2000
Number of Samples:	One

Samples Taken by: Rob Peters

Thank you for your prompt response to this request.

Sincerely,



Rob Peters
Maintenance/Operations Supervisor

RP:dlg
Enclosures

Received By:
Christina Hwa
8/10/00 10:20am
Fed to



Bulk Asbestos Analysis

(EPA Method 600/R-93-116, Visual Area Estimation)

San Francisco • Los Angeles • Minneapolis / St. Paul

Chico Unified School Dist
Rob Peters2455 Carmichael Drive
Chico, CA 95928Client ID: 2921
Report Number: B022205
Date Received: 08/10/00
Date Analyzed: 08/11/00
Date Printed: 08/11/00
First Reported: 08/11/00


Job ID / Site: Chico Sr./Jr. High School-Unit 900/K

FASI Job ID: 2921-25

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
1	10041565						
Layer: Beige Cementitious Material		Chrysotile	2 %				
Layer: Paint			ND				
Total Composite Values of Fibrous Components:		Asbestos:(2%)	Cellulose (2%)	Fibrous Glass (ND)			
Comment:Collected on 8/9/00							
2	10041566						
Layer: Off-White Cementitious Material		Chrysotile	2 %				
Layer: Paint			ND				
Total Composite Values of Fibrous Components:		Asbestos:(2%)	Cellulose (ND)	Fibrous Glass (ND)			
Comment:Collected on 8/9/00							

James Flores, Laboratory Supervisor, Hayward Laboratory

Note: Limit of Quantification ('LOQ') = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.



Results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) named in this report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written request from the client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified.

C: Asbestos Analysis

Maintenance and Operations
2455 Carmichael Drive
Chico, CA 95928
Phone: (530) 891-3095
Fax: (530) 891-3190

Chico Unified School District

August 9, 2000

Forensic Analytical Specialties, Inc.
3777 Depot Road, Suite 409
Hayward, CA 94545

2921-25

Re: Chico Junior High School Unit K Window Putty and
Chico Senior High School Unit 900 Window Putty

To Whom It May Concern:

Please test the enclosed window putty samples from both Chico Junior and Chico Senior High Schools for asbestos and lead. Please fax the results to me as soon as soon as they are available. My fax number is (530) 891-3190.

Site Sampled:	Chico Senior High School
Location:	Unit 900 Window Putty
Date Sampled:	August 9, 2000
Number of Samples:	One

Site Sampled:	Chico Junior High School
Location:	Unit K Window Putty
Date Sampled:	August 9, 2000
Number of Samples:	One

Samples Taken by: Rob Peters

Thank you for your prompt response to this request.

Sincerely,



Rob Peters
Maintenance/Operations Supervisor

RP:dlg
Enclosures

Received By:
Christina Hsu
8/10/00 10:20am
Fed to



Bulk Asbestos Analysis

(EPA Method 600/R-93-116, Visual Area Estimation)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B024478
Date Received: 11/09/00
Date Analyzed: 11/10/00
Date Printed: 11/10/00
First Reported: 11/10/00

Job ID / Site: Chico High School

FASI Job ID: 2921-30

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
C-1	10057234						
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				


Total Composite Values of Fibrous Components: Asbestos:(ND) Cellulose (Trace%) Fibrous Glass (40%)

C-2	10057235						
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				

Total Composite Values of Fibrous Components: Asbestos:(ND) Cellulose (Trace%) Fibrous Glass (40%)

C-3	10057236						
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				

Composite Values of Fibrous Components: Asbestos:(ND) Cellulose (Trace%) Fibrous Glass (40%)





Forensic Analytical

San Francisco • Los Angeles • Minneapolis / St. Paul

Bulk Asbestos Analysis

(EPA Method 600/R-93-116, Visual Area Estimation)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B024478
Date Received: 11/09/00
Date Analyzed: 11/10/00
Date Printed: 11/10/00
First Reported: 11/10/00

Job ID / Site: Chico High School

FASI Job ID: 2921-30

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
---------------	------------	---------------	------------------	---------------	------------------	---------------	------------------

C-4 10057237

Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND

Total Composite Values of Fibrous Components: Asbestos:(ND) Cellulose (Trace%) Fibrous Glass (40%)

C-5 10057238

Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND

Total Composite Values of Fibrous Components: Asbestos:(ND) Cellulose (Trace%) Fibrous Glass (40%)

C-6 10057239

Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND
Layer: Black Tar	ND
Layer: Black Felt	ND

Total Composite Values of Fibrous Components: Asbestos:(ND) Cellulose (55%) Fibrous Glass (Trace%)



Forensic Analytical

San Francisco • Los Angeles • Minneapolis / St. Paul

Bulk Asbestos Analysis

(EPA Method 600/R-93-116, Visual Area Estimation)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B024478
Date Received: 11/09/00
Date Analyzed: 11/10/00
Date Printed: 11/10/00
First Reported: 11/10/00

Job ID / Site: Chico High School

FASI Job ID: 2921-30

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
C-7	10057240						
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				

Composite Values of Fibrous Components: Asbestos:(ND) Cellulose (55%) Fibrous Glass (Trace%)

C-8	10057241						
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				

Total Composite Values of Fibrous Components: Asbestos:(ND) Cellulose (55%) Fibrous Glass (Trace%)



Forensic Analytical

San Francisco • Los Angeles • Minneapolis / St. Paul

Bulk Asbestos Analysis

(EPA Method 600/R-93-116, Visual Area Estimation)

Chico Unified School Dist
Ron Jones

2455 Carmichael Drive
Chico, CA 95928

Client ID: 2921
Report Number: B024478
Date Received: 11/09/00
Date Analyzed: 11/10/00
Date Printed: 11/10/00
First Reported: 11/10/00

Job ID / Site: Chico High School

FASI Job ID: 2921-30

Sample Number	Lab Number	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer	Asbestos Type	Percent in Layer
C-9	10057242						
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				

Total Composite Values of Fibrous Components: Asbestos:(ND) Cellulose (55%) Fibrous Glass (Trace%)

C-10	10057243						
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				
Layer: Black Tar			ND				
Layer: Black Felt			ND				

Total Composite Values of Fibrous Components: Asbestos:(ND) Cellulose (55%) Fibrous Glass (Trace%)

James Flores, Laboratory Supervisor, Hayward Laboratory

Note: Limit of Quantification ('LOQ') = 1%. 'Trace' denotes the presence of asbestos below the LOQ. 'ND' = 'None Detected'.

Analytical results and reports are generated by Forensic Analytical at the request of and for the exclusive use of the person or entity (client) named in this report. Results, reports or copies of same will not be released by Forensic Analytical to any third party without prior written request from the client. This report applies only to the sample(s) tested. Supporting laboratory documentation is available upon request. This report must not be reproduced except in full, unless approved by Forensic Analytical. The client is solely responsible for the use and interpretation of test results and reports requested from Forensic Analytical. This report must not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government. Forensic Analytical is not able to assess the degree of hazard resulting from materials analyzed. Forensic Analytical reserves the right to dispose of all samples after a period of thirty (30) days, according to all state and federal guidelines, unless otherwise specified.



BULK SAMPLE REQUEST FORM

IT NAME & ADDRESS: 2921 \ Chlco Unified School District 31 2455 Carmichael Drive Chlco, CA 95928		PHONE: (916) 891- FAX: (916) 891-3190	DATE:
		Circle the Method and Turn Around Time 24 hr/12hr/24hr/48hr/Ext	Results Needed:
		PLM: Standard / Point Count	
		CONTACT:	
P.O.#	JOB #	AA/Flame AA/Furnace ICP	
SITE:		METALS:	

SAMPLE NUMBER	DATE COLLECTED	SAMPLE LOCATION/DESCRIPTION
CSH 1	11/7	UNIT S ROOF
CSH 2	11/7	UNIT S ROOF
CSH 3	11/7	UNIT S ROOF
CSH 4	11/7	UNIT S ROOF
CSH 5	11/7	UNIT S ROOF
CSH 6	11/7	UNIT H ROOF
CSH 7	11/7	UNIT H ROOF
CSH 8	11/7	UNIT H ROOF
CSH 9	11/7	UNIT H ROOF
CSH #10	11/7	UNIT H ROOF

Sampled by: ROB PETERS	Date: 11/7/00 Time: 8:00 AM
Relinquished by:	Received By: [Signature] 11/9/00
Date/Time:	Date/Time: Sealed Condition (circle one) YES / NO
Relinquished by:	Received By:
Date/Time:	Date/Time: Sealed Condition (circle one) YES / NO

30

Maintenance and Operations
2455 Carmichael Drive
Chico, CA 95928
Phone: (530) 891-3095
Fax: (530) 891-3190

Chico Unified School District

November 7, 2000

Forensic Analytical Specialties, Inc.
3777 Depot Road, Suite 409
San Francisco, CA 94545

Re: Roof Samples

To Whom It May Concern:

Please test the enclosed roof samples for asbestos. Please fax the results to me. My fax number is (530) 891-3190.

Site Sampled:	Chico High School
Date Sampled:	November 7, 2000
Number of Samples:	Ten
Sample #1:	S-Wing Roof
Sample #2:	S-Wing Roof
Sample #3:	S-Wing Roof
Sample #4:	S-Wing Roof
Sample #5:	S-Wing Roof
Sample #6:	Unit H Roof
Sample #7:	Unit H Roof
Sample #8:	Unit H Roof
Sample #9:	Unit H Roof
Sample #10:	Unit H Roof
Samples Taken by:	Rob Peters

Thank you for your prompt response to this request.

Sincerely,



Rob Peters

DISTRICT Chico Unified School DistrictDATE 8/9/00SCHOOL Chico Senior HighINSPECTOR Robert Peters

BLDG.	HOMOG. MAT.#	ASBESTOS MATERIAL	LOCATION	CONDITION: CODE & COMMENTS	
A	Mud Jnt	5-10	Darkroom - Attic	1-4	
A	Mesh wrap	15-20	Darkroom - Attic	11	
A, B, C	Tran panl	Assumed	Red painted panels along walkways, janitor closets, rr, stairwells	1-4 (S) PANELS PAINTED WHITE	
B	12" VFT	1-5	All rooms	1-4	✓
C	12" VFT	1-5	All rooms	1-4	✓
400	12' VFTs	1-5	Library Entry & Office Area	1-4	✓
400	Mud jnt	5-10	Library Attic	1-4 Repaired Inv. 95-235L	✓
500	Tran panl	Assumed	2 - Kilns	1-4	✓
500	Mud jnts	5-10	Fine Arts	1-4	✓
500	Mud jnts	5-10	Room F-1	1-4	✓

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTEDMISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)

DISTRICT Chico Unified School District

DATE

SCHOOL Chico Senior High

INSPECTOR Robert Peters

HOMOG. ASBESTOS

CONDITION: CODE & COMMENTS

BLDG. MAT.# MATERIAL LOCATION

S	Heat Shld paper	75-80	Rm S-3	7	
S	Bl countr	Assumed	Science Rooms	1-4	
S	Mud jnts	5-10	All Rooms	1-4	
S	9" VFT Bg	1-5	All Rooms	1-4	
S	PW Str	65-70	Rm S-5 Storeroom	2-7 - WO issued (S)(C)	
H 700	Bir Ins	25-35	Home Ec Boiler Room	1-4	
700	TOC	1-5	Music wing hall ceiling	7	
700	TOC	1-5	Instrument storage room	1-4 - WO issued	
700	9" VFT yl	5-10	Music Wing Hall	7	
700	Tran Peg Board	15-20	Custodial & Band Practice Rooms	(broken & missing) 2-4 WO issued	NEED WO TO REPAIR
700	Hold tank	Assumed	Home Ec Heater Room	1-4	

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)

CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)

ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTED

MISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)

DISTRICT Chico Unified School District

DATE _____

SCHOOL Chico Senior HighINSPECTOR Robert Peters

HOMOG. ASBESTOS

BLDG.	MAT.#	MATERIAL	LOCATION	CONDITION: CODE & COMMENTS
700	PW Str	75-80	Home Ec Storage Closet	1-4
700	PW Str	75-80	2nd Home Ec Storage Closet	1-4
700	PW Cnr	75-80	Home Ec Storage Closet	1-4
700	Door Fill	25-35	Home Ec Heater Room	1-4
700	PW Str	5-10	Home Ec Heater Room	1-4
700	Tran pipe	Assumed	Home Ec Heater Room	1-4
700	PW Aircel	Assumed	Under Choral Room Risers	10
700	PW Debris	Assumed	Under Choral Room Risers	7
700	T-O-C	1-5	Band Rm Off., Choral Rm Stor	1-4
700	9" VFTs	5-10	Choral Rm under Risers, Band Rm Off, Choral Rm Stor	1-4
1000	PW Str	35-40	Auto Shop, Loft, Woodshop	2-4 (1) -Tee (2) End WO issued

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTEDMISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)

DISTRICT Chico Unified School District DATE _____SCHOOL Chico Senior HighINSPECTOR Robert Peters

HOMOG. ASBESTOS

CONDITION: CODE & COMMENTS

BLDG. MAT.# MATERIAL LOCATION

1000	Breeching	Assumed	Woodshop Finishing Room	1-4	
900	PW Str	50-55	Girls/Boys Locker Room	1-4	Blocked off
900	PW Str	50-55	Girls/Boys Boil rm crawl sp	1-4	Blocked off
900	Tank Wrap	1-5	Gym Boiler Room	7	
900	Mud Jnt	5-10	Gym Boiler Room	7	
900	Boiler rm gasket	85-90	Gym Boiler Room	7	
900	Wall & ceil plas	1-5	All rooms except Boiler Room	Retested - no asbestos	
800	9" VFT Gy	1-5	Kitchen & MPR	5-7 tiles missing/broken (5) (4)	
800	TOC	1-5	All Rooms	5-6 water stains (painted) (1)	
800	Tran panl	Assumed	Snack Bar	1-4	
800	Tran panl	Assumed	Stage & Cafe	1-4	

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTEDMISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)

DISTRICT Chico Unified School District

DATE _____

SCHOOL Chico Senior HighINSPECTOR Robert Peters

HOMOG. ASBESTOS

BLDG.	MAT.#	MATERIAL	LOCATION	CONDITION: CODE & COMMENTS
800	Mud Jnts	5-10	Under stage	1-4
800	9" VFT		Under stage	1-4
800	PW Str	35-40	Custodial Room	1-4
800	Mud Jnts	5-10	Restroom Teacher's Lounge	1-4
800	Tran Pipe	Assumed	Water Heater Rm (2 pipes)	1-4
1100	Wall Plas	1-5	Ag Classroom 2 (space 3)	1-4
1100	Tran Panl	15-20	Ag Shop Welding Booth	2-4 to 1-4 (2-3-00)
1100	12" VFTs	Assumed	Classroom	1-4
1100	Tran Pipe	Assumed	Ag Shop (2 pipes)	1-4

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTEDMISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)

DISTRICT Chico Unified School DistrictDATE February 3, 2000SCHOOL Chico Senior HighINSPECTOR Robert Peters

BLDG.	HOMOG. MAT.#	ASBESTOS MATERIAL	LOCATION	CONDITION: CODE & COMMENTS
A	Mud Jnt	5-10	Darkroom - Attic	1-4
A	Mesh wrap	15-20	Darkroom - Attic	11
A,B,C	Tran panl	Assumed	Red painted panels along walkways, janitor closets, rr, stairwells	1-4
B	12" VFT	1-5	All rooms	1-4
C	12" VFT	1-5	All rooms	1-4
400	12' VFTs	1-5	Library Entry & Office Area	1-4
400	Mud jnt	5-10	Library Attic	1-4 Repaired Inv. 95-235L
500	Tran panl	Assumed	2 - Kilns	1-4
500	Mud jnts	5-10	Fine Arts	1-4
500	Mud jnts	5-10	Room F-1	1-4

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTEDMISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)

DISTRICT Chico Unified School DistrictDATE February 3, 2000SCHOOL Chico Senior HighINSPECTOR Robert Peters

BLDG.	HOMOG. MAT.#	ASBESTOS MATERIAL	LOCATION	CONDITION: CODE & COMMENTS
S	Heat Shld paper	75-80	Rm S-3	7
S	Bl countr	Assumed	Science Rooms	1-4
S	Mud jnts	5-10	All Rooms	1-4
S	9" VFT Bg	1-5	All Rooms	1-4
S	PW Str	65-70	Rm S-5 Storeroom	2-7 - WO issued
H 700	Bir Ins	25-35	Home Ec Boiler Room	1-4
700	TOC	1-5	Music wing hall ceiling	7
700	TOC	1-5	Instrument storage room	1-4 - WO issued
700	9" VFT yl	5-10	Music Wing Hall	7
700	Tran Peg Board	15-20	Custodial & Band Practice Rooms	(broken & missing) 2-4 WO issued
700	Hold tank	Assumed	Home Ec Heater Room	1-4

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)

CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)

ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTED

MISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)

DISTRICT Chico Unified School DistrictDATE February 3, 2000SCHOOL Chico Senior HighINSPECTOR Robert Peters

BLDG.	HOMOG. MAT.#	ASBESTOS MATERIAL	LOCATION	CONDITION: CODE & COMMENTS	
700	PW Str	75-80	Home Ec Storage Closet	1-4	
700	PW Str	75-80	2nd Home Ec Storage Closet	1-4	
700	PW Cnr	75-80	Home Ec Storage Closet	1-4	
700	Door Fill	25-35	Home Ec Heater Room	1-4	
700	PW Str	5-10	Home Ec Heater Room	1-4	
700	Tran pipe	Assumed	Home Ec Heater Room	1-4	
700	PW Aircel	Assumed	Under Choral Room Risers	10	
700	PW Debris	Assumed	Under Choral Room Risers	7	
700	T-O-C	1-5	Band Rm Off., Choral Rm Stor	1-4	
700	9" VFTs	5-10	Choral Rm under Risers, Band Rm Off, Choral Rm Stor	1-4	
1000	PW Str	35-40	Auto Shop, Loft, Woodshop	2-4 (1) -Tee (2) End WO issued	

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)

CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)

ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTED

MISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)

DISTRICT Chico Unified School DistrictDATE February 3, 2000SCHOOL Chico Senior HighINSPECTOR Robert Peters

BLDG.	HOMOG. MAT.#	ASBESTOS MATERIAL	LOCATION	CONDITION: CODE & COMMENTS
1000	Breeching	Assumed	Woodshop Finishing Room	1-4
900	PW Str	50-55	Girls/Boys Locker Room	1-4 Blocked off
900	PW Str	50-55	Girls/Boys Boil rm crawl sp	1-4 Blocked off
900	Tank Wrap	1-5	Gym Boiler Room	7
900	Mud Jnt	5-10	Gym Boiler Room	7
900	Boiler rm gasket	85-90	Gym Boiler Room	7
900	Wall & ceil plas	1-5	All rooms except Boiler Room	Retested - no asbestos
800	9" VFT Gy	1-5	Kitchen & MPR	5-7 tiles missing/broken
800	TOC	1-5	All Rooms	5-6 water stains (painted)
800	Tran panl	Assumed	Snack Bar	1-4
800	Tran panl	Assumed	Stage & Cafe	1-4

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTEDMISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)

DISTRICT Chico Unified School DistrictDATE February 3, 2000SCHOOL Chico Senior HighINSPECTOR Robert Peters

BLDG.	HOMOG. MAT.#	ASBESTOS MATERIAL	LOCATION	CONDITION: CODE & COMMENTS
800	Mud Jnts	5-10	Under stage	1-4
800	9" VFT		Under stage	1-4
800	PW Str	35-40	Custodial Room	1-4
800	Mud Jnts	5-10	Restroom Teacher's Lounge	1-4
800	Tran Pipe	Assumed	Water Heater Rm (2 pipes)	1-4
1100	Wall Plas	1-5	Ag Classroom 2 (space 3)	1-4
1100	Tran Panl	15-20	Ag Shop Welding Booth	2-4 to 1-4 (2-3-00)
1100	12" VFTs	Assumed	Classroom	1-4
1100	Tran Pipe	Assumed	Ag Shop (2 pipes)	1-4

CONDITION CODES

GENERAL CONDITION: (1) GOOD (2) DAMAGED (3) SIGNIFICANTLY DAMAGED (25% OR MORE)CHANGE IN CONDITION: (4) NO (5) YES (IF YES, EXPLAIN UNDER COMMENTS)ABATED: (6) REPAIRED (7) REMOVED (8) ENCAPSULATED (9) ENCLOSED (10) ISOLATED & RESTRICTEDMISC: (11) INACCESSIBLE, NO SURVEILLANCE DATA (12) OTHER (EXPLAIN UNDER COMMENTS)