

INSPECTION DOCUMENTS

LEA: CHICO UNIFIED SCHOOL DISTRICT

SCHOOL: NEAL DOW

DATE OF INSPECTION: MARCH 29, 1988

INSPECTOR: JAMES E SHARP, SR.

ACCREDITATION: U. C. BERKELEY, P. A. I. C. #4


*(name of inspector)

UNIVERSITY OF CALIFORNIA BERKELEY UNIVERSITY EXTENSION

This is to certify that

James E Sharp

has attended and satisfactorily passed the exam
for the course

Building Inspection and Management Planning for Asbestos

November 16-20, 1987

This certification is valid until:

November 20, 1988

November 18 and 20, 1987

Exam dates

4

Certificate number



Vivian Sutcher

Assistant Dean
University Extension

Deborah D.

Program Director
Pacific Asbestos Information Center

UNIVERSITY OF CALIFORNIA BERKELEY UNIVERSITY EXTENSION

This is to certify that

JAMES E. SHARP

has attended the refresher course
for building inspectors and management planners,

Advanced Topics in Building Inspection and Management Planning

December 13, 1988

Certificate number: 4

Valid until: December 13, 1989



Vivian Sitcher
Assistant Dean
University Extension

Deborah Dill
Program Director
Pacific Asbestos Information Center

SUMMARY OF FRIABLE AND NON-FRIABLE ACBM BY BUILDING

CS CODE

04 61424 6003040

SC-GCL

NEAL DOW ELEMENTARY SCHOOL

SCHOOL PHONE NUMBER

(209) 891 3110

ADDRESS

(Number)

(Street)

(City)

(Zip Code)

NUMBER OF BUILDINGS

5

LINE	BUILDING NAME (Indicate Address if Different From Above)	NONE	CHECK ONE			
			ACBM		ASSUMED ACBM	
			FRIABLE	NON-FRIABLE	FRIABLE	NON-FRIABLE
1.	UNIT A		X	X		X
2.	UNIT B		X	X		X
3.	UNIT C			X		X
4.	PORTABLE	X				
5.	TRAILER	X				
6.						
7.						
8.						
9.						
10.						
11.						
12.						
13.						
14.						
15.						
16.						
17.						
18.						
19.						
20.						

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Lab Number: 8809432
Sample Number: DOW-01
Site: Neal Dow.

Analyst: BS

Location: Kindergarten Quad, Unit C - 12" acoustic tile, Room 9.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Tan, fibrous material associated with a white, particulate substance (core sample).

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile
Amosite
Crocidolite

<1
<1
<1
%

<1 %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose
Mineral Wool
Polyethylene

85-90
<1
<1
%

85-90 %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates

10-15
10-15
%
%
%

10-15 %

Analyst:

Daniel Valance for BS

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:

Hazard Management Services, Inc.

P.O. Box 7012

Modesto, CA 95355

Client Number: 141

Report Number: 7103

Date Received: 04/05/88

Date Examined: 04/13/88

Lab Number: 8809433

Sample Number: DOW-02A

Site: Neal Dow.

Analyst: BS

Location: Kindergarten Quad - center section, Room 3 - T-0-0.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white, semi-fibrous material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	1-5	%
Amosite	<1	%
Crocidolite	<1	%

1-5 %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	%
Mineral Wool	<1	%
Polyethylene	<1	%

Trace %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	95-99	%
--------------------------	-------	---

95-99 %

Analyst:

David Valore for BS

Supervisor:

DE

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95353

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Lab Number: 8809434
Sample Number: DOW-02B
Site: Neal Dow.

Analyst: BS

Location: Kindergarten Quad - center section, Room 9 - T-O-C.

P.O.: Chico Unified School District, Neal Dow

Gross Description: Off-white, semi-fibrous material (core sample).

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	1-5	3
Amosite	<1	3
Crocidolite	<1	3

1-5 3

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	3
Mineral Wool	<1	3
Polyethylene	<1	3

Trace 3

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	95-99	3
--------------------------	-------	---

95-99 3

Analyst:

David Kalene for BS

Supervisor:

DE

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Lab Number: 8809435
Sample Number: DOW-02C
Site: Neal Dow.

Analyst: BE

Location: Kindergarten Quad - center section, Room 9 - T-O-C.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white, semi-fibrous material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	1-5	%
Amosite	<1	%
Crocidolite	<1	%

1-5 3

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	%
Mineral Wool	<1	%
Polyethylene	<1	%

Trace 3

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	95-99	%
--------------------------	-------	---

95-99 1

Analyst:

David Kalanick

Supervisor:

DE

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:

Hazard Management Services, Inc.

P.O. Box 7012

Modesto, CA 95355

Client Number: 146

Report Number: 7103

Date Received: 04/05/88

Date Examined: 04/13/88

Lab Number: 8809436

Sample Number: DOW-03

Site: Neal Dow.

Analyst: PS

Location: Kindergarten Quad, Unit C - 9" VET, Beige.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Beige floor tile associated with some black,
tar adhesive.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	1-5	%
Amosite	<1	%
Crocidolite	<1	%

1-5 %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	%
Mineral Wool	<1	%
Polyethylene	<1	%

Trace %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	95-99	%
--------------------------	-------	---

95-99 %

Analyst:

David Kalane for PS

Supervisor:

DE

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Lab Number: 8809437
Sample Number: DOW-04
Site: Neal Dow.

Analyst: BS

Location: Roundhouse Quad - around center ceiling, Unit B -
ceiling tiles 2x4 panels.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Tan, fibrous material.

MICROSCOPIE DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	5-10	3
Amosite	<1	3
Crocidolite	<1	3

5-10 3

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	40-45	3
Mineral Wool	20-25	3
Polyethylene	<1	3

60-70 3

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	20-35	3
--------------------------	-------	---

20-25 3

Analyst:

David Valcane for BS

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Lab Number: 8809438
Sample Number: Dow-05A
Site: Neal Dow.

Analyst: BS

Location: Roundhouse Quad - center ceiling area, Unit B - T-O-C.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white, semi-fibrous material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	1-5	%
Amosite	<1	%
Crocidolite	<1	%

1-5 %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	%
Mineral Wool	<1	%
Polyethylene	<1	%

Trace %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	95-99	%
--------------------------	-------	---

95-99 %

Analyst:

Daniel Williams for BS

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Lab Number: 8809439
Sample Number: DOW-05B
Site: Neal Dow

Analyst: BS

Location: Roundhouse Quad - center ceiling area, Unit B - T-O-C.

P.O.: Chico Unified School District, Neal Dow

Gross Description: Off-white, semi-fibrous material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	1-5	3
Amosite	<1	3
Crocidolite	<1	3

1-3 3

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	3
Mineral Wool	<1	3
Polyethylene	<1	3

Trace

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	95-99	3
--------------------------	-------	---

95-99 3

Analyst:

David Valcarlos

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:

Hazard Management Services, Inc.

P.O. Box 7012

Modesto, CA 95355

Client Number: 146

Report Number: 7102

Date Received: 04/05/88

Date Examined: 04/13/88

Lab Number: 8809440

Sample Number: DOW-05C

Site: Neal Dow.

Analyst: BE

Location: Roundhouse Quad - center ceiling area, Unit B - T-O-C.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white, semi-fibrous material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	1-5	%
Amosite	<1	%
Crocidolite	<1	%

1-5 %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	%
Mineral Wool	<1	%
Polyethylene	<1	%

Trace %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	95-99	%
--------------------------	-------	---

95-99 %

Analyst:

David Kahan BE

Supervisor:

DE

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:

Hazard Management Services, Inc.

P.O. Box 7012

Modesto, CA 95355

Client Number: 146

Report Number: 7103

Date Received: 04/05/88

Date Examined: 04/13/88

Lab Number: 8909441

Sample Number: DOW-06

Site: Neal Dow.

Analyst: BS

Location: Roundhouse Quad Attic, Unit B - Pipewrap corners.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white, semi-fibrous powder.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	25-30	%
Amosite	<1	%
Crocidolite	<1	%

25-30 3

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	<1	%
Mineral Wool	25-30	%
Polyethylene	<1	%

25-30 3

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	40-50	%
--------------------------	-------	---

40-50 3

Analyst:

David Kahan

Supervisor:

DK

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:

Hazard Management Services, Inc.

P.O. Box 7012

Modesto, CA 95355

Client Number: 146

Report Number: 7103

Date Received: 04/05/88

Date Examined: 04/13/88

Lab Number: 8809442

Analyst: BS

Sample Number: DOW-07

Site: Neal Dow.

Location: Administration Office, Unit A - 12" ceiling tile.
acoustic.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Tan, fibrous material (core sample).

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

<1 %

Chrysotile

<1

%

Amosite

<1

%

Crocidolite

<1

%

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

85-90 %

Cellulose

85-90

%

Mineral Wool

<1

%

Polyethylene

<1

%

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

10-15 %

Unspecified Particulates

10-15

%

Analyst:

Daniel Kalane for BS

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 145
Report Number: 7102
Date Received: 04/05/88
Date Examined: 04/13/88

Lab Number: 8809443
Sample Number: DOW-02
Site: Neal Dow.

Analyst: BS

Location: Administration Office and Hall, Unit A - 9" VET,
beige.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Beige floor tile.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	1-5	%
Amosite	<1	%
Crocidolite	<1	%

1-5 %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	%
Mineral Wool	<1	%
Polyethylene	<1	%

Trace %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	95-99	%
--------------------------	-------	---

95-99 %

Analyst:

Daniel Kahan for BS

Supervisor:

DE

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:

Hazard Management Services, Inc.

P.O. Box 7012

Modesto, CA 95355

Client Number: 146

Report Number: 7103

Date Received: 04/05/88

Date Examined: 04/13/88

Lab Number: 8809444

Analyst: BS

Sample Number: DOW-09

Site: Neal Dow.

Location: Administration Office - north wall and west wall - 12" wall tile, acoustic.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Tan fibrous material associated with white paint.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

<1 %

Chrysotile	<1	%
Amosite	<1	%
Crocidolite	<1	%

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

85-90 %

Cellulose	85-90	%
Mineral Wool	Trace	%
Polyethylene	<1	%

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

10-15 %

Unspecified Particulates	10-15	%
--------------------------	-------	---

Analyst:

David Kalman BS

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95356

Client Number: 136
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Lab Number: 8809445
Sample Number: DOW-10
Site: Neal Dow.

Analyst: BS

Location: Restroom - Nurses's office area, Unit A - Linoleum.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white linoleum material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	5-10	3
Amosite	<1	3
Crocidolite	<1	3

5-10 3

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	3
Mineral Wool	<1	3
Polyethylene	<1	3

Trace 3

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	90-95	3
--------------------------	-------	---

90-95 3

Analyst:

Daniel Valencia for BS

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:

Hazard Management Services, Inc.

P.O. Box 7012

Modesto, CA 95355

Client Number: 146

Report Number: 7102

Date Received: 04/05/88

Date Examined: 04/13/88

Lab Number: 8809446

Sample Number: DOW-11

Site: Neal Dow.

Analyst: PS

Location: Administration hallway attic, Unit A - Patching pipes.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white to grey aggregate patching material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	25-30	3
Amosite	<1	3
Crocidolite	<1	3

25-30 3

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	<1	3
Mineral Wool	30-35	3
Polyethylene	<1	3

30-35 3

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	35-45	3
--------------------------	-------	---

35-45 3

Analyst:

David Valasek to PS

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7102
Date Received: 04/05/88
Date Examined: 04/13/88

Analyst: BS

Lab Number: 8809447
Sample Number: DOW-12
Site: Neal Dow.

Location: Administration hallway attic, Unit A - Pipewrap
corner.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Tan semifibrous powder.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	25-30	%
Amosite	<1	%
Crocidolite	<1	%

25-30 %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	<1	%
Mineral Wool	35-40	%
Polyethylene	<1	%

35-40 %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	30-40	%
--------------------------	-------	---

30-40 %

Analyst:

David Kalan

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Analyst: BS

Lab Number: 8809443
Sample Number: DOW-12
Site: Neal Dow.

Location: Hall attic, Unit A - PW straight.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Grey fibrous powder material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:		35-40	4
Chrysotile	<1	3	
Amosite	35-40	3	
Crocidolite	<1	3	
		3	
TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:		Trace	3
Cellulose	Trace	3	
Mineral Wool	<1	3	
Polyethylene	<1	3	
		3	
TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:		60-65	4
Unspecified Particulates	60-65	3	
		3	
		3	
		3	

Analyst:

David K. Kline for BS

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Analyst: BS

Lab Number: 8809449
Sample Number: DOW-14
Site: Neal Dow.

Location: Boiler Room, Unit A - Large diameter pipewrap
straight.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Grey fibrous powder material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile

<1 %

Amosite

35-40 %

Crocidolite

<1 %

35-40 %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose

Trace %

Mineral Wool

<1 %

Polyethylene

<1 %

Trace %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates

60-65 %

60-65 %

Analyst:

David Kalanick

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Analyst: BS

Lab Number: 8809450
Sample Number: DOW-15
Site: Neal Dow.

Location: Boiler Room, Unit A - Small diameter pw straight.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Grey semi-fibrous material-core sample.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:			30-35	%
Chrysotile	<1	%		
Amosite	30-35	%		
Crocidolite	<1	%		
TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:			<1	%
Cellulose	<1	%		
Mineral Wool	<1	%		
Polyethylene	<1	%		
TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:			65-70	%
Unspecified Particulates	65-70	%		

Analyst:

Supervisor: DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/13/88

Lab Number: 8809451
Sample Number: DOW-16
Site: Neal Dow.

Analyst: BS

Location: Boiler Room, Unit A - Breaching on exhaust of boiler.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white fibrous material-core sample.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	1-5	%
Amosite	20-25	%
Crocidolite	<1	%

20-30 %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	45-50	%
Mineral Wool	<1	%
Polyethylene	<1	%

45-50 %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	30-35	%
--------------------------	-------	---

30-35 %

Analyst:

David Kalan for BS

Supervisor:

JK

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA Bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%), are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:

Hazard Management Services, Inc.

P.O. Box 7012

Modesto, CA 95355

Client Number: 146

Report Number: 7103

Date Received: 04/05/88

Date Examined: 04/13/88

Lab Number: 8809452

Sample Number: DOW-17A

Site: Neal Dow.

Analyst: BS

Location: Boiler Room, Unit A - T-O-C.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white ceiling material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	Trace	%
Amosite	<1	%
Crocidolite	<1	%

Trace %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	%
Mineral Wool	<1	%
Polyethylene	<1	%

Trace %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	98-99	%
--------------------------	-------	---

98-99 %

Analyst:

David Valcarlos

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:

Hazard Management Services, Inc.

P.O. Box 7012

Modesto, CA 95355

Client Number: 146

Report Number: 7102

Date Received: 04/05/88

Date Examined: 04/13/88

Lab Number: 8809453

Sample Number: DCW-172

Site: Neal Dow.

Analyst: BS

Location: Boiler Room, Unit A - T-O-C.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white ceiling material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	Trace	3
Amosite	<1	3
Crocidolite	<1	3

Trace 3

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	3
Mineral Wool	<1	3
Polyethylene	<1	3

Trace 3

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	98-99	3
--------------------------	-------	---

98-99 3

Analyst:

David Valance for BS

Supervisor:

De

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:
Hazard Management Services, Inc.

P.O. Box 7012
Modesto, CA 95355

Client Number: 146
Report Number: 7103
Date Received: 04/05/88
Date Examined: 04/12/88

Lab Number: 8809454
Sample Number: DOW-17C
Site: Neal Dow.

Analyst: BE

Location: Boiler Room, Unit A - T-O-C.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white ceiling material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	Trace	3
Amosite	<1	4
Crocidolite	<1	3

Trace 3

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	Trace	3
Mineral Wool	<1	2
Polyethylene	<1	3

Trace 3

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	98-99	3
--------------------------	-------	---

98-99 3

Analyst:

David Kalam

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

BULK ASBESTOS ANALYSIS REPORT

FOR

Client:

Hazard Management Services, Inc.

P.O. Box 7012

Modesto, CA 95355

Client Number: 146

Report Number: 7103

Date Received: 04/05/88

Date Examined: 04/13/88

Lab Number: 8809455

Sample Number: DOW-18

Site: Neal Dow.

Analyst: BS

Location: Portable Rooms 21 & 22 - 2x4 panels, ceiling.

P.O.: Chico Unified School District, Neal Dow.

Gross Description: Off-white fibrous material.

MICROSCOPIC DESCRIPTION:

TOTAL ASBESTOS PRESENT:

Chrysotile	<1	%
Amosite	<1	%
Crocidolite	<1	%

<1 %

TOTAL NON-ASBESTOS FIBROUS MATERIAL PRESENT:

Cellulose	75-80	%
Mineral Wool	<1	%
Polyethylene	<1	%

75-80 %

TOTAL NON-ASBESTOS NON-FIBROUS MATERIAL PRESENT:

Unspecified Particulates	5-10	%
Perlite	10-15	%

20-15 %

Analyst:

David Kalawa

Supervisor:

DC

COMMENTS: Analysis employs Polarized Light Microscopy with Dispersion Staining, and is performed by an analyst qualified under the EPA bulk asbestos proficiency testing program. Samples with no observable asbestiform minerals are designated as containing less than one percent (<1%) asbestos. Samples in which asbestiform minerals have been observed, but exist in concentrations of less than one percent (<1%) are designated as present in "trace" amounts.

Forensic Analytical Specialties, Inc.

Dear Local Educational Assistance Official:


Forensic Analytical Specialties, Inc., in accordance with the Asbestos Hazards Emergency Response Act, has received Accredited Laboratory status for the purpose of analyzing suspected asbestos-containing materials in schools. Verification of this accreditation can be found in the Federal Register/Vol. 53, No. 169/August 31, 1988, page 33611.

The analysis of each sample received by our laboratory becomes the responsibility of one of our qualified microscopists. Different samples within a single group or in different groups submitted by the same client may be assigned to different analysts. In order to simplify the reporting process, the analyst responsible for each sample is listed by initials in the upper right-hand corner of each report and the report is signed solely by the lab supervisor. To satisfy any questions regarding signatures by each analyst involved in sample characterization, listed below are the signatures corresponding to the analyst's initials which you may find on your particular set of reports:

<u>Initials</u>	<u>Analyst Name</u>	<u>Analyst Signature</u>
BB	Brent Beadnell	<i>Brent Beadnell</i>
MF	Michelle Fox	<i>Michelle Fox</i>
DK	David Kahane	<i>David Kahane</i>
JM	Jeff Malaihollo	<i>Jeffrey A. Malaihollo</i>
DN	David Nesbitt	<i>David J. Nesbitt</i>
SAS	Stephen A. Shaffer	<i>Stephen A. Shaffer</i>
BT	Boyd Taylor	<i>Boyd Taylor</i>

I hope that this additional information will help clarify any issues regarding laboratory result reporting practices under AHERA. We wish you good luck in the effective implementation of your Hazard Management Plan.


Sincerely,



David Kahane
Director of Environmental Services
Forensic Analytical Specialties, Inc.

Consulting and Laboratory Services in the Forensic and Environmental Health Sciences

3777 Depot Road, Suite 406 - 408, Hayward, CA 94545 415/887-8828 FAX 415/887-4218





- 21 -

9220

Stephen A. Shaffer
Forensic Analytical Specialties, Inc.
3777 Depot Road Suite 408
Hayward, CA 94545

SUBJECT: EPA Interim Laboratory Accreditation for Laboratories
Which Offer Analysis of Bulk Samples for Asbestos

Dear Laboratory Director:

The U.S. Environmental Protection Agency (EPA) has completed its review of the results of the second round of analyses in the EPA "Interim Asbestos Bulk Sample Analysis Quality Assurance Program." I am pleased to inform you that your laboratory has successfully classified each of four bulk samples submitted to your facility as either asbestos-containing or nonasbestos-containing. Since each sample was correctly classified, a status of "accredited" has been assigned to your laboratory. As you are aware, each laboratory is also given a numerical score which does not affect your accredited status. The numerical score reflects your laboratory's performance in determining the quantity and type of asbestos in the asbestos-containing samples. Your laboratory's score is 100%.

As announced in the FEDERAL REGISTER of March 29, 1988 (see enclosed copy), the second round of the EPA Interim Program is the last planned round of EPA accreditation. Laboratories which are accredited in the second round of this program will be considered accredited until January 12, 1989. The National Bureau of Standards (NBS) will begin formal operation of the National Voluntary Laboratory Accreditation Program (NVLAP) for laboratories which conduct analyses of bulk samples for asbestos by polarized light microscopy (PLM) in October 1988. Applications for participation in this program are currently being accepted. You may contact Dr. Larry Gallowin of NBS at (301)975-4022 for enrollment information. An exception to the EPA deadline of January 12, 1989 has been made for laboratories which are accredited in the second EPA round and have enrolled in the NUS program by September 30, 1988. These laboratories will be considered accredited by EPA until NBS has completed its first evaluation of an individual laboratory's performance. The enclosed copy of the FEDERAL REGISTER notice details the period of transition from EPA accreditation to NBS accreditation. Please note that a laboratory currently accredited by EPA must enter the NBS program and receive accreditation from NBS to continue analysis of bulk samples from school buildings.

Should you have any questions regarding the current EPA round of accreditation, you may contact Bruce Harvey of Research Triangle Institute at (919)541-6169. Thank you for your participation in the program.

Sincerely,

Martin P. Halper, Director
Exposure Evaluation Division (TS-722)

ADDITIONAL MANAGEMENT PLAN DATA

SAMPLING PROTOCOL

Where friable surfacing materials were encountered, the following sampling protocol was followed.

1. The homogeneous sampling area was divided into nine equal areas.
2. Random numbers were taken from a source (EPA's Sampling Strategy Booklet).
3. Three samples were collected at or near the center of the selected areas which totaled less than 1,000 square feet, five for 1,000 to 5,000 square feet, and seven or more for friable homogeneous areas greater than 5,000 square feet.

Where non-friable samples were collected, the following sampling protocol was followed:

1. Surfacing - three or more samples were collected, generally in non-conspicuous locations from each homogeneous material.
2. TSI - three or more samples were taken from homogeneous materials.
3. Miscellaneous - one or more samples were taken from miscellaneous materials in a manner sufficient to determine the asbestos content of each homogeneous material.

In some cases materials were assumed to contain asbestos. This was done with materials which always contain asbestos (transite or aircell insulation) or with materials which had been identified as ACM in a previous survey.

Client Number		Report Number		HAZARD MANAGEMENT SERVICES, INC.		CHICO UNIFIED SCHOOL DIST.	
Received By		Date Rec'd		Bill To:		District or Business	
				P.O. Box 7012, Modesto, Ca 95355		School <i>Spauld</i>	
				Billing Address:		OR	
				Collected by: <i>JES</i>		Bldg <i>JES</i>	
Reported Results		Date/Time/By		Date		Sent to Lab by:	
				LAB Request: % Asbestos By PLM		date <i>4/1/93</i>	

FAI Lab#	Sample #HMS-	I - I page No	MATERIALS/LOCATION	% Asbestos
	<i>DOW-01</i>		M: <i>12" rebar tile - Rm 9</i> L: <i>Knightsbridge Quad - Unit C</i>	<i><1</i>
	<i>DOW-02A</i>		M: <i>T-D-C</i> L: <i>Knightsbridge Quad - Center Section Rm 9</i>	<i>1-5</i>
	<i>DOW-02B</i>		M: <i>T-D-C</i> L: <i>Knightsbridge Quad - Center Section Rm 9</i>	<i>1-5</i>
	<i>DOW-02C</i>		M: <i>T-D-C</i> L: <i>Knightsbridge Quad - Center Section Rm 9</i>	<i>1-5</i>
	<i>DOW-03</i>		M: <i>9" VET - Rm 9</i> L: <i>Knightsbridge Quad - Unit C</i>	<i>1-5</i>
	<i>DOW-04A</i>		M: <i>Ceiling T-D-C like 2x4 panels</i> L: <i>Knightsbridge Quad - Center Section - Unit B</i>	<i>5-10</i>
	<i>DOW-05A</i>		M: <i>T-D-C</i> L: <i>Knightsbridge Quad - Center Section - Unit B</i>	<i>1-5</i>
	<i>DOW-05B</i>		M: <i>T-D-C</i> L: <i>Knightsbridge Quad - Center Section - Unit B</i>	<i>1-5</i>
	<i>DOW-05C</i>		M: <i>T-D-C</i> L: <i>Knightsbridge Quad - Center Section - Unit B</i>	<i>1-5</i>
	<i>DOW-06</i>		M: <i>Pipe rack area</i> L: <i>Knightsbridge Quad - Unit B</i>	<i>25-30</i>

BULK SAMPLES

3777 Depot Rd: Suite 408

Hayward, Ca. 94545 (415) 887-8828

Page 2 of 3

HAZARD MANAGEMENT SERVICES, INC.		CHILD UNIFIED SCHOOL DIST	
Client Number	Report Number	District or Business	
Received By	Date Rec'd	School <u>Head View</u>	
Reported Results		Date	Sent to Lab by:
Date/Time/By		3/29/88	JES
LAB Request: % Asbestos By PLM		Bldg	
Collected by:		Date	
JE SHARP		3/29/88	

FAS Lab#	Sample #HMS-	I - 1 page No	MATERIALS/LOCATION	% Asbestos
	DOW-07		M: 12" Coil tile - acoustical L: Admin. Office - Unit A	< 1
	DOW-08		M: 9" VFT Pipe L: Admin. Office & Hall - Unit A	1-5
	DOW-09		M: 12" wall tile - acoustical L: Admin. Office - acoustical & wood wall	< 1
	DOW-10		M: <u>Acoustical</u> L: Reception - Admin. Office - Unit A	5-10
	DOW-11		M: <u>Acoustical Pipes</u> L: Admin. Hallway Office - Unit A	25-30
	DOW-12		M: <u>Pipes</u> L: Admin. Hallway Office - Unit A	25-30
	DOW-13		M: <u>PW straight</u> L: Hall Office - Unit A	35-40
	DOW-14		M: <u>Large diameter sewer pipe straight</u> L: <u>Gravel Room Unit A</u>	35-40
	DOW-15		M: <u>Small diameter sewer straight</u> L: <u>Gravel Room - Unit A</u>	30-35
	DOW-16		M: <u>Gravel Room on opposite of pipes</u> L: <u>Gravel Room - Unit A</u>	20-30

DOW 17A, B, C

M: TDC

L: Supp RR & Gravel Room - Classroom Hallway and (East)

TRACE

Asbestos

FORENSIC ANALYTICAL SPECIALTIES INC. - ASBESTOS ANALYSIS LABORATORY REQUEST FORM

BULK SAMPLES

3777 Depot Rd: Suite 408

Hayward, Ca. 94545 (415) 887-8828

Page 3 of 3[illegible]

APPLICATION NO.

SITE SUMMARY

ORDERED BY: THOMSON & MENOBICKS / ARCHITECTS & PLANNERS/ (916) 342-5669 234 WEST THIRD STREET CHICO, CALIF. 95928